

Printing date 19.03.2025 Version number 40 (replaces version 39) Revis

Revision: 17.12.2024

SECTION 1: Identification of the substance/mixture and of the company/ undertaking

· 1.1 Product identifier

- Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616
- **1.2 Relevant identified uses of the substance or mixture and uses advised against** No further relevant information available.
- · Application of the substance / the mixture Adhesive

• **1.3 Details of the supplier of the safety data sheet** • **Manufacturer/Supplier:** Bison International Dr.A.F.Philipsstraat 9 NL-4462 EW Goes PO Box 160 NL-4460 AD Goes tel. +31 88 3235700 fax. +31 88 3235800

e mail: sds@boltonadhesives.com

· Further information obtainable from: PSRA

· 1.4 Emergency telephone number:

Bison and Griffon products: +31 88 3235700. Operating hours mo-fr 08:00h-17:00h (CET) UHU products: + 49 (0) 30/19240 (Notruf). Operating hours mo-fr 08:00h-17:00h (CET)

For detailed information contact the national Poison Centre @ https://poisoncentres.echa.europa.eu/appointed-bodies

SECTION 2: Hazards identification

2.1 Classification of the substance or mixture
 Classification according to Regulation (EC) No 1272/2008

GHS02 flame

Flam. Liq. 2 H225 Highly flammable liquid and vapour.



Eye Irrit. 2 H319 Causes serious eye irritation. STOT SE 3 H336 May cause drowsiness or dizziness.

2.2 Label elements

Labelling according to Regulation (EC) No 1272/2008

The product is classified and labelled according to the CLP regulation.

Hazard pictograms



(Contd. on page 2)



Safety data sheet according to Regulation (EC) No 1907/2006, Article 31 Printing date 19.03.2025 Version number 40 (replaces version 39) Revision: 17.12.2024 Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616 (Contd. of page 1) Signal word Danger · Hazard-determining components of labelling: Acetone Ethyl acetate · Hazard statements H225 Highly flammable liquid and vapour. H319 Causes serious eye irritation. H336 May cause drowsiness or dizziness. Precautionary statements P101 If medical advice is needed, have product container or label at hand. P102 Keep out of reach of children. P210 Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. P261 Avoid breathing vapours. P370+P378 In case of fire: Use to extinguish: Water haze, Alcohol resistant foam, Fireextinguishing powder, Carbon dioxide. P403+P233 Store in a well-ventilated place. Keep container tightly closed. P501 Dispose of contents/container in accordance with national regulations. Additional information: EUH066 Repeated exposure may cause skin dryness or cracking. Product contains: Reportable explosives precursors. Making available, introduction, possession and use according to Regulation (EU) 2019/1148, Article 9. Labelling of packages where the contents do not exceed 125 ml Hazard pictograms GHS02 GHS07 · Signal word Danger · Hazard-determining components of labelling: Acetone Ethvl acetate · Hazard statements H336 May cause drowsiness or dizziness. Precautionary statements P101 If medical advice is needed, have product container or label at hand. P102 Keep out of reach of children. P210 Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Avoid breathing vapours. P261 P403+P233 Store in a well-ventilated place. Keep container tightly closed. Dispose of contents/container in accordance with national regulations. P501 2.3 Other hazards Results of PBT and vPvB assessment • **PBT:** Not applicable. · vPvB: Not applicable. FH

(Contd. on page 3)



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

(Contd. of page 2)

SECTION 3: Composition/information on ingredients · 3.2 Mixtures · Description: Adhesive · Dangerous components: 50-100% CAS: 67-64-1 Acetone ♦ Flam. Liq. 2, H225; ♦ Eye Irrit. 2, H319; STOT SE 3, H336, EUH066 EINECS: 200-662-2 Index number: 606-001-00-8 Reg.nr.: 01-2119471330-49-XXXX CAS: 141-78-6 10-25% Ethyl acetate ♦ Flam. Liq. 2, H225; ♦ Eye Irrit. 2, H319; STOT SE 3, H336, EUH066 EINECS: 205-500-4 Index number: 607-022-00-5 Reg.nr.: 01-2119475103-46-XXXX CAS: 1065336-91-5 Reaction mass of Bis(1,2,2,6,6-pentamethyl-4-≥0.025-<0.1% EC number: 915-687-0 piperidyl) sebacate and Methyl 1,2,2,6,6-Reg.nr.: 01-2119491304-40pentamethyl-4-piperidyl sebacate 🗞 Repr. 2, H361f; 🚯 Aquatic Acute 1, H400; XXXX Aquatic Chronic 1, H410; 🔿 Skin Sens. 1A, H317

Additional information: For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

- · 4.1 Description of first aid measures
- · General information: No special measures required.
- After inhalation:

Supply fresh air; consult doctor in case of complaints.

- No special measures required.
- After skin contact: Generally the product does not irritate the skin.
- · After eye contact:

Rinse opened eye for several minutes under running water. If symptoms persist, consult a doctor.

- After swallowing: If symptoms persist consult doctor.
- **4.2 Most important symptoms and effects, both acute and delayed** No further relevant information available.
- **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- Suitable extinguishing agents:
- Water haze

Alcohol resistant foam

- Fire-extinguishing powder
- Carbon dioxide

· For safety reasons unsuitable extinguishing agents: Water with full jet

(Contd. on page 4)

EU



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

• 5.2 Special hazards arising from the substance or mixture

- No further relevant information available.
- 5.3 Advice for firefighters
- · Protective equipment: No special measures required.
- Additional information

Cool endangered receptacles with water spray.

Collect contaminated fire fighting water separately. It must not enter the sewage system.

SECTION 6: Accidental release measures

• 6.1 Personal precautions, protective equipment and emergency procedures Wear protective equipment. Keep unprotected persons away.

- 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up: Send for recovery or disposal in suitable receptacles.

Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust). Ensure adequate ventilation.

6.4 Reference to other sections

See Section 7 for information on safe handling.

See Section 8 for information on personal protection equipment.

See Section 13 for disposal information.

SECTION 7: Handling and storage

· 7.1 Precautions for safe handling

Ensure good interior ventilation, especially at floor level. (Fumes are heavier than air). Ensure good ventilation/exhaustion at the workplace. Prevent formation of aerosols.

• Information about fire - and explosion protection: Keep ignition sources away - Do not smoke. Protect against electrostatic charges.

· 7.2 Conditions for safe storage, including any incompatibilities

· Storage:

· Requirements to be met by storerooms and receptacles: Store in a cool location.

- · Information about storage in one common storage facility: Not required.
- · Further information about storage conditions:
- Keep container tightly sealed.

Store in cool, dry conditions in well sealed receptacles.

- Storage class: 3
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· 8.1 Control parameters

· Ingredients with limit values that require monitoring at the workplace:

67-64-1 Acetone

IOELV Long-term value: 1210 mg/m³, 500 ppm

(Contd. on page 5)

(Contd. of page 3)



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

141-78-6	Ethyl acetate		(Contd. of pag	
	-	: 1468 mg/m ³ , 400 ppm		
		: 734 mg/m ³ , 200 ppm		
DNELS	<u> </u>			
67-64-1 A	cetone			
Oral		al, longterm exposition	62 mg/kg bw/day	
Dermal		al, longterm exposition	186 mg/kg bw/day	
		ermal, longterm exposition	62 mg/kg bw/day	
Inhalative		ative, shortterm exposition	2420 mg/m ³	
		ative, longterm exposition	1210 mg/m ³	
	Consumer, inhalative, longterm exposition		-	
141-78-6 I	Ethyl acetate		5	
Oral	•	al, longterm exposition	4.5 mg/kg bw/day	
Dermal	Worker, derm	al, longterm exposition	63 mg/kg bw/day	
	Consumer, de	ermal, longterm exposition	37 mg/kg bw/day	
Inhalative	Worker, inhal	ative, shortterm exposition	1468 mg/m ³	
	Worker, inhal	ative, longterm exposition	734 mg/m³	
	Consumer DN	IEL, acute inhalation	734 mg/m³	
	Consumer, in	halative, longterm exposition	367 mg/m³	
1065336-9			amethyl-4-piperidyl) sebacate and Meth	
		pentamethyl-4-piperidyl sel		
Oral		al, longterm exposition	0.18 mg/kg bw/day	
Dermal		al, longterm exposition	1.8 mg/kg bw/day	
		ermal, longterm exposition	0.9 mg/kg bw/day	
Inhalative		ative, longterm exposition	1.27 mg/m ³	
	Consumer, in	halative, longterm exposition	0.31 mg/m³	
PNECs				
67-64-1 A				
Fresh wate	er	10.6 mg/l		
Fresh wate	er sediment	30.4 mg/kg dry weight		
Marine wa		1.06 mg/l		
Marine se	diment	3.04 mg/kg dry weight		
Soil		29.5 mg/kg		
-	eatment plant	-		
Sporadic r		21 mg/l		
	Ethyl acetate			
Fresh wate		0.24 mg/l		
	er sediment	1.15 mg/kg dry weight		
		0.024 mg/l		
Marine wa	timont	0.115 mg/kg dry weight		
Marine wa Marine see Soil		0.148 mg/kg		



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substant preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation acoding to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 n 	<u> </u>	4	250						(Contd. of pa	age
1,2,2,6,6-pentamethyl-4-piperidyl sebacate Fresh water 0.0022 mg/l Fresh water sediment 1.05 mg/kg dry weight Marine sediment 0.11 mg/kg dry weight Soil 0.21 mg/kg Sewage treatment plant 1 mg/l Sporadic release 0.009 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Reseptatory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter A Hand protection Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves <th>-</th> <th>-</th> <th>-</th> <th></th> <th></th> <th></th> <th></th> <th></th> <th></th> <th></th>	-	-	-							
Fresh water sediment 1.05 mg/kg dry weight Marine water 0.00022 mg/l Marine sediment 0.11 mg/kg dry weight Soil 0.21 mg/kg Sewage treatment plant 1 mg/l Sporadic release 0.009 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Adpropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes. Avoid contact with the eyes. Avoid contact with the eyes and skin. Recommended filter device for short term use: Filter A Hand protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the pro							ridyl) so	ebacate	e and Met	thy
Marine water 0.00022 mg/l Marine sediment 0.11 mg/kg dry weight Soil 0.21 mg/kg Sewage treatment plant 1 mg/l Sporadic release 0.009 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Recommended filter device for short term use: Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm <td>.0022 mg/</td> <td>0</td> <th>).0022 mg/l</th> <td></td> <th></th> <th></th> <th></th> <th></th> <th></th> <td></td>	.0022 mg/	0).0022 mg/l							
Marine sediment 0.11 mg/kg dry weight Soil 0.21 mg/kg Sewage treatment plant 1 mg/l Sporadic release 0.009 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter A Hand protection Solevent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile ruber	.05 mg/kg	ment 1	l.05 mg/kg dry we	/eight						
Soil 0.21 mg/kg Sewage treatment plant 1 mg/l Sporadic release 0.009 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substance preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material:	.00022 mg	0).00022 mg/l							
Sewage treatment plant 1 mg/l 0.009 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetr	.11 mg/kg	0).11 mg/kg dry we	/eight						
Sporadic release 0.009 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter AX Filter A Hand protection Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time	.21 mg/kg	0).21 mg/kg							
Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 n	mg/l	nt plant 1	l mg/l							
Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 n	.009 mg/l	0).009 mg/l							
Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 10 m	-		-	iring the m	making w	ere used	as basis	3.		
Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 10 m		ontrols								
General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substance preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 n	controls		, controls No fur	rther data	a; see sec	tion 7.				
The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substance preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m					al protec	tive equ	ipment			
Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter AX Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m										
Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 n					ed to whe	n handlir	ng chem	icals.		
Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 n					a tha ina ar					
Do not inhale gases / fumes / aerosols. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substance preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m					Juning					
Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substant preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m				OI WOIK.						
Avoid contact with the eyes and skin. Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substance preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m										
Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substant preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m										
Recommended filter device for short term use: Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m										
Filter AX Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substand preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m					f insufficie	ent ventila	ation.			
Filter A Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substance preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m	ice for sh	filter devi	vice for short ter	rm use:						
 Hand protection Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substant preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m 										
Solvent resistant gloves The glove material has to be impermeable and resistant to the product/ the substant preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m										
The glove material has to be impermeable and resistant to the product/ the substant preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m										
preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion a degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m	to be imp		to be impermea	able and	resistar	nt to the	product	t/ the s	ubstance	/ th
degradation Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m			•				•			
Material of gloves Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m	erial on co	glove mat	terial on conside	eration of	the pene	tration tir	nes, rate	es of dif	ffusion and	d th
Recommended thickness of the material: > 0,12 mm Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m										
Butyl rubber, BR Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m	of the meet		of the meterial >	0.10 mm						
Nitrile rubber, NBR Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m	or the mat	lickness	or the material: >	> 0, 12 mm	n					
Recommended thickness of the material: > 0,7 mm Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m		R								
Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 m (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 m	of the mat		of the material: >	> 0.7 mm						
For the mixture of chemicals mentioned below the penetration time has to be at least 10 n (Permeation according to EN 374 Part 3: Level 1). For the mixture of chemicals mentioned below the penetration time has to be at least 120 n				,						
For the mixture of chemicals mentioned below the penetration time has to be at least 120 n				celow the	penetrat	tion time	has to b	be at lea	ast 10 mir	nute
					penetrati	on time h	has to be	e at leas	st 120 mir	nute
(Permeation according to EN 374 Part 3: Level 4).	=N 374 Pa		EN 374 Part 3: L	_evel 4).						
Eye/face protection		lion								
Tightly sealed goggles	odales	spaled a	logales							
rightly scaled goggles	Jyyies	sealed y	oggies							

(Contd. on page 7)

EU



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

(Contd. of page 6)

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

Goggles recommended during refilling · Body protection: Solvent resistant protective clothing

Physical stateFluidColour:According to product specificationOdour:CharacteristicOdour threshold:Not determined.Melting point or initial boiling point andUndetermined.boiling range55 °CFlammabilityHighly flammable.Lower and upper explosion limitLower:Lower:2.1 Vol %Upper:13 Vol %Flash point:-17 °CAuto-ignition temperature:460 °CDecomposition temperature:Not determined.pHNot determined.Viscosity:Kinematic viscosityKinematic viscosityNot determined.SolubilityVapour pressure at 20 °C:vapour pressure at 20 °C:800 hPaDensity and/or relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.Partition coefficient n-octanol/water (log value)0.898 g/cm³Relative densityNot determined.Vapour densityNot determined.Partition coefficient no cellisityNot determined.Partition coefficient no cellisity0.898 g/cm³Partition coefficient no cellisityNot determined.Partition coefficient no cellisityNot determined.Partition coefficient no cellisityNot determined.Promoti and or relevationAll relevant physical data were determined for th mixture. All non-determined data are no me as urable or not relevant for th characterization of the mixture.Appearance:Fluid	9.1 Information on basic physical and chemic	al properties
Colour:According to product specificationOdour:CharacteristicOdour threshold:Not determined.Melting point or initial boiling point andboiling rangeBoiling range55 °CFlammabilityHighly flammable.Lower:2.1 Vol %Upper:13 Vol %Flash point:-17 °CAuto-ignition temperature:460 °CDecomposition temperature:Not determined.PHNot determined.Viscosity:Not determined.Kinematic viscosityNot determined.Oyamic at 20 °C:3000 mPasSolubilityNot determined.Vapour pressure at 20 °C:800 hPaDensity and/or relative densityNot determined.Vapour pressure at 20 °C:0.898 g/cm³Relative densityNot determined.Vapour densityNot determined.Vapour and/or relative densityNot determined.Vapour densityNot determined.Vapour netative idensity0.898 g/cm³SolubilityNot determined.Vapour netative idensityNot determined.Vapour densityNot determined.Vapour netative idensityNot determined.Vapour netative idensityNot determined.Partition temperature:Product is not selfigniting.Partition coefficient noctation on protection of health and environment, and on safety.Product is not selfigniting.Papearance:From:FluidForm:FluidIgnition temperature:Produc	General Information	
Odour:CharacteristicOdour threshold:Not determined.Odour threshold:Undetermined.Boiling point or initial boiling point andUndetermined.boiling range55 °CFlammabilityHighly flammable.Lower and upper explosion limit1Lower:2.1 Vol %Upper:13 Vol %Flash point:-17 °CAuto-ignition temperature:460 °CDecomposition temperature:Not determined.pHNot determined.Viscosity:Not determined.Kinematic viscosityNot determined.Dynamic at 20 °C:3000 mPasSolubilityNot determined.Value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 20 °C:800 hPaDensity and/or relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for th mixture. All non-determined data are no meas urable or not relevant for th characterization of the mixture.Appearance:Form:FluidForm:FluidImportant information on protection of health and environment, and on safety.Product is not selfigniting.Ignition temperature:Product is not explosive. However, formation of explosive air/vapour mixtures are possible.Solvent content:Solvent content:	•	
Odour threshold:Not determined.Metting point/freezing point:Undetermined.Metting point or initial boiling point and boiling range55 °CFlammabilityHighly flammable.Lower:2.1 Vol %Upper:13 Vol %Flash point:-17 °CAuto-ignition temperature:460 °CDecomposition temperature:Not determined.Viscosity:Not determined.Viscosity:Not determined.Viscosity:Not determined.Value)Not determined.Value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:0.898 g/cm³Pelative densityNot determined.Vapour pressure at 50 °C:0.898 g/cm³Pative densityNot determined.Vapour pressure at 50 °C:0.898 g/cm³Pelative densityNot determined.Vapour freative densityNot determined.Vapour freative densityNot determined.9.2 Other informationAll relevant physical data were determined for th mixture. All non-determined data are no me as urable or not relevant for th characterization of the mixture.Appearance:From:FluidForm:FluidImportant information on protection of health and environment, and on safety.Product is not selfigniting.Ignition temperature:Product is not selfigniting.Solvent content:Solvent content:		
Melting point/freezing point:Undetermined.Boiling point or initial boiling point and boiling range55 °CFlammabilityHighly flammable.Lower:2.1 Vol %Upper:13 Vol %Flash point:-17 °CAuto-ignition temperature:460 °CDecomposition temperature:Not determined.PHNot determined.Viscosity:*********************************		
Boiling point or initial boiling point and boiling range 55 °C Flammability Highly flammable. Lower and upper explosion limit 2.1 Vol % Upper: 13 Vol % Flash point: -17 °C Auto-ignition temperature: 460 °C Decomposition temperature: Not determined. pH Not determined. Viscosity: Kinematic viscosity Kinematic viscosity Not determined. Oynamic at 20 °C: 3000 mPas Solubility vater: water: Not determined. Vapour pressure at 20 °C: 233 hPa Vapour pressure at 20 °C: 800 hPa Density and/or relative density Density and/or relative density Density at 20 °C: 0.898 g/cm³ Relative density Not determined. 9.2 Other information All relevant physical data were determined data are nor me as urable or not relevant for the characterization of the mixture. Appearance: From: Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Ignition temperature: Product is not e		
boiling range55 °CFlammabilityHighly flammable.Lower and upper explosion limitLower:2.1 Vol %Upper:13 Vol %Flash point:-17 °CAuto-ignition temperature:460 °CDecomposition temperature:Not determined.pHNot determined.Viscosity:Not determined.Kinematic viscosityNot determined.Oynamic at 20 °C:3000 mPasSolubilityNot determined.value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:800 hPaDensity and/or relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined data are norm me as urable or not relevant for th characterization of the mixture.Appearance:FluidForm:FluidImportant information on protection of health and environment, and on safety.Product is not selfigniting.Ignition temperature:Product is not selfigniting.Explosive properties:Product is not selfigniting.Solvent content:Solvent content:		Undetermined.
Flammability Highly flammable. Lower and upper explosion limit 2.1 Vol % Lower: 2.1 Vol % Upper: 13 Vol % Flash point: -17 °C Auto-ignition temperature: 460 °C Decomposition temperature: Not determined. pH Not determined. Viscosity: Kinematic viscosity Kinematic viscosity Not determined. Oynamic at 20 °C: 3000 mPas Solubility water: water: Not determined. Vapour pressure at 20 °C: 233 hPa Vapour pressure at 50 °C: 800 hPa Density and/or relative density Not determined. Vapour pressure at 50 °C: 0.898 g/cm³ Relative density Not determined. Vapour refersure at 50 °C: 0.898 g/cm³ Relative density Not determined. Vapour density <th></th> <th></th>		
Lower and upper explosion limit 2.1 Vol % Lower: 2.1 Vol % Upper: 13 Vol % Flash point: -17 °C Auto-ignition temperature: 460 °C Decomposition temperature: Not determined. pH Not determined. Viscosity: Not determined. Kinematic viscosity Not determined. Solubility Not determined. vater: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Vapour pressure at 20 °C: 233 hPa Vapour pressure at 50 °C: 800 hPa Density and/or relative density Not determined. Vapour pressure at 50 °C: 800 hPa Density at 20 °C: 0.898 g/cm³ Relative density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for th mixture. All non-determined data are nor me as urable or not relevant for th characterization of the mixture. Important information on protection of health and environment, and on safety. Product is not selfigniting.		
Lower:2.1 Vol %Upper:13 Vol %Flash point:-17 °CAuto-ignition temperature:460 °CDecomposition temperature:Not determined.pHNot determined.Viscosity:Kinematic viscosityKinematic viscosityNot determined.Dynamic at 20 °C:3000 mPasSolubilityNot determined.value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:800 hPaDensity and/or relative density0.898 g/cm³Relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.Vapour density0.898 g/cm³Relative densityNot determined.SolubilityNot determined.Vapour densityNot determined.Vapour densityNot determined.Vapour densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for th mixture. All non-determined data are not measurable or not relevant for th characterization of the mixture.Appearance:FluidForm:FluidImportant information on protection of health 	•	Highly flammable.
Upper:13 Vol %Flash point:-17 °CAuto-ignition temperature:460 °CDecomposition temperature:Not determined.pHNot determined.Viscosity:Not determined.Kinematic viscosityNot determined.Oynamic at 20 °C:3000 mPasSolubilityNot miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:800 hPaDensity and/or relative density0.898 g/cm³Pensity at 20 °C:0.898 g/cm³Relative densityNot determined.9.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture.Appearance:FluidForm:FluidImportant information on protection of health and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product is not explosive. However, formation explosive air/vapour mixtures are possible.Solvent content:Solvent content:		
Flash point: -17 °C Auto-ignition temperature: 460 °C Decomposition temperature: Not determined. pH Not determined. Viscosity:		
Auto-ignition temperature: 460 °C Decomposition temperature: Not determined. pH Not determined. Viscosity: Not determined. Kinematic viscosity Not determined. Dynamic at 20 °C: 3000 mPas Solubility vater: water: Not determined. Partition coefficient n-octanol/water (log value) Vapour pressure at 20 °C: 233 hPa Vapour pressure at 50 °C: 800 hPa Density and/or relative density Density and/or relative density Density at 20 °C: 0.898 g/cm³ Relative density Not determined. Vapour pressure at 50 °C: 800 hPa Density and/or relative density Not determined. Vapour density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. Appearance: Fluid Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Explosive properties:	••	-
Decomposition temperature: Not determined. pH Not determined. Viscosity: ************************************		
pHNot determined.Viscosity:Not determined.Kinematic viscosityNot determined.Dynamic at 20 °C:3000 mPasSolubilityNot miscible or difficult to mix.Partition coefficient n-octanol/water (logNot determined.value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:800 hPaDensity and/or relative densityDensity at 20 °C:Density at 20 °C:0.898 g/cm³Relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.Vapour densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are not me as urable or not relevant for the characterization of the mixture.Appearance:FluidForm:FluidImportant information on protection of health and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product is not explosive. However, formation explosive air/vapour mixtures are possible.Solvent content:Solvent content:	Auto-ignition temperature:	460 °C
Viscosity: Not determined. Viscosity: Not determined. Vanamic at 20 °C: 3000 mPas Solubility Not miscible or difficult to mix. Partition coefficient n-octanol/water (log Not determined. Value) Not determined. Vapour pressure at 20 °C: 233 hPa Vapour pressure at 50 °C: 800 hPa Density and/or relative density Density at 20 °C: Density at 20 °C: 0.898 g/cm³ Relative density Not determined. Vapour density Not determined. • Partition component and on safety. All relevant physical data were determined for the mixture. All non-determined data are not me as urable or not relevant for the characterization of the mixture. • Appearance: Fluid • Form: Fluid • Important information on protection of health and environment, and on safety. Product is not selfigniting. • Ignition temperature: Product is not explosive. However, formation explosive air/vapour mixtures are possible. • Solvent content: Solvent content:	Decomposition temperature:	Not determined.
Viscosity: Not determined. Not at 20 °C: 3000 mPas Solubility Not miscible or difficult to mix. Partition coefficient n-octanol/water (log Not determined. Value) Not determined. Vapour pressure at 20 °C: 233 hPa Vapour pressure at 50 °C: 800 hPa Density and/or relative density 0.898 g/cm³ Patitive density Not determined. Vapour density Not determined. Vapour density 0.898 g/cm³ Pelative density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are not me as urable or not relevant for the characterization of the mixture. Appearance: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation on explosive air/vapour mixtures are possible. Solvent content: Solvent content:	pH	Not determined.
Kinematic viscosityNot determined.Dynamic at 20 °C:3000 mPasSolubilityNot miscible or difficult to mix.Partition coefficient n-octanol/water (logVot determined.Value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:800 hPaDensity and/or relative density0.898 g/cm³Density at 20 °C:0.898 g/cm³Vapour densityNot determined.Vapour densityNot determined.• Vapour densityNot determined.• Vapour densityNot determined.• Partition coefficient n-octanol/water (logNot determined.• Vapour pressure at 50 °C:800 hPa• Density and/or relative densityNot determined.• Density at 20 °C:0.898 g/cm³• Partition densityNot determined.• Vapour densityNot determined.• Vapour densityNot determined.• Partition densityFluid• Important information on protection of health and environment, and on safety.Product is not selfigniting.• Explosive properties:Product is not explosive. However, formation on explosive air/vapour mixtures are possible.• Solvent content:Product is not explosive are possible.		
Dynamic at 20 °C: 3000 mPas Solubility Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Vapour pressure at 20 °C: 233 hPa Vapour pressure at 50 °C: 800 hPa Density and/or relative density Density at 20 °C: Density at 20 °C: 0.898 g/cm³ Relative density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for th mixture. All non-determined data are no measurable or not relevant for th characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Ignition temperature: Product is not explosive. However, formation explosive air/vapour mixtures are possible. Solvent content: Solvent content:		Not determined.
Solubility Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Vapour pressure at 20 °C: 233 hPa Vapour pressure at 50 °C: 800 hPa Density and/or relative density Density and/or relative density Density at 20 °C: 0.898 g/cm³ Relative density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are not me as urable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Ignition temperature: Product is not explosive. However, formation explosive air/vapour mixtures are possible. Solvent content: Solvent content:		
water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:800 hPaDensity and/or relative density0.898 g/cm³Density at 20 °C:0.898 g/cm³Relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined data are not measurable or not relevant for the characterization of the mixture.Appearance:Form:Form:FluidIgnition temperature:Product is not selfigniting.Ignition temperature:Product is not selfigniting.Solvent content:Solvent content:		
Partition coefficient n-octanol/water (log value) Not determined. Vapour pressure at 20 °C: 233 hPa Vapour pressure at 50 °C: 800 hPa Density and/or relative density 0.898 g/cm³ Density at 20 °C: 0.898 g/cm³ Pensity at 20 °C: Not determined. Psite at 20 °C: Pinsity at 20 °C: Psite at 20 °C: Pinsity at 20 °C: Product is not explosive. However, formation of e	•	Not miscible or difficult to mix.
value)Not determined.Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:800 hPaDensity and/or relative density0.898 g/cm³Density at 20 °C:0.898 g/cm³Relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are not me as urable or not relevant for the characterization of the mixture.Appearance:Form:Form:FluidImportant information on protection of health and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product is not explosive. However, formation or explosive air/vapour mixtures are possible.Solvent content:Solvent content:		
Vapour pressure at 20 °C:233 hPaVapour pressure at 50 °C:800 hPaDensity and/or relative density0.898 g/cm³Density at 20 °C:0.898 g/cm³Relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are norme as urable or not relevant for the characterization of the mixture.Appearance:FluidForm:FluidImportant information on protection of health and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product is not explosive. However, formation or explosive air/vapour mixtures are possible.Solvent content:Solvent content:		Not determined
Vapour pressure at 50 °C: 800 hPa Density and/or relative density 0.898 g/cm³ Density at 20 °C: 0.898 g/cm³ Relative density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are norm easurable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation or explosive air/vapour mixtures are possible. Solvent content: Solvent content:		
Density and/or relative density Density at 20 °C: 0.898 g/cm³ Relative density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are not measurable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation or explosive air/vapour mixtures are possible. Solvent content: Solvent content:		
Density at 20 °C: 0.898 g/cm³ Relative density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are normeasurable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation on explosive air/vapour mixtures are possible. Solvent content: Solvent content:		
Relative density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are normeasurable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation or explosive air/vapour mixtures are possible. Solvent content: Solvent content:		0.898 g/cm ³
Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are normeasurable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Ignition temperature: Product is not explosive. However, formation or explosive air/vapour mixtures are possible. Solvent content: Solvent content:		
9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are normeasurable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Fluid Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation or explosive air/vapour mixtures are possible.		
 Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Explosive properties: Solvent content: 		Not determined.
Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation of explosive air/vapour mixtures are possible. Solvent content: Solvent content:		mixture. All non-determined data are no measurable or not relevant for th
Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation of explosive air/vapour mixtures are possible. Solvent content: Solvent content:	Appearance:	
and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product is not explosive. However, formation of explosive air/vapour mixtures are possible.Solvent content:Solvent content:		Fluid
and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product is not explosive. However, formation of explosive air/vapour mixtures are possible.Solvent content:Solvent content:	Important information on protection of health	
Ignition temperature: Product is not selfigniting. Explosive properties: Product is not explosive. However, formation of explosive air/vapour mixtures are possible. Solvent content: Solvent content:		
• Explosive properties: Product is not explosive. However, formation explosive air/vapour mixtures are possible. • Solvent content:		Product is not selfigniting.
		Product is not explosive. However, formation of
Organic solvents: 78.4 %	Solvent content:	
	Organic solvents:	78.4 %



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

	(Contd. of page
· VOC (EC)	78.41 %
Solids content:	21.5 %
· Change in condition	
· Evaporation rate	Not determined.
· Information with regard to physical haz	ard
classes	
· Explosives	Void
Flammable gases	Void
Aerosols	Void
· Oxidising gases	Void
· Gases under pressure	Void
· Flammable liquids	Highly flammable liquid and vapour.
Flammable solids	Void
· Self-reactive substances and mixtures	Void
· Pyrophoric liquids	Void
· Pyrophoric solids	Void
· Self-heating substances and mixtures	Void
· Substances and mixtures, which emit	
flammable gases in contact with water	Void
· Oxidising liquids	Void
Oxidising solids	Void
· Organic peroxides	Void
· Corrosive to metals	Void
· Desensitised explosives	Void

SECTION 10: Stability and reactivity

• 10.1 Reactivity No further relevant information available.

- 10.2 Chemical stability
- Thermal decomposition / conditions to be avoided:
- No decomposition if used according to specifications.
- **10.3 Possibility of hazardous reactions** No dangerous reactions known.
- 10.4 Conditions to avoid No further relevant information available.
- **10.5 Incompatible materials:** No further relevant information available.
- **10.6 Hazardous decomposition products:** Danger of forming toxic pyrolysis products.

		hazard classes as defined in Regulation (EC) No 1272/2008 d on available data, the classification criteria are not met.
LD/LC50	values rele	evant for classification:
67-64-1 A	cetone	
Oral	LD50	5800 mg/kg (rat)
Dermal	LD50	>15800 mg/kg (rat)
Inhalative	LC50/4 h	76 mg/l (rat)

EU



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

		(Contd. of page
141-78-6 E		
Oral	LD50	4934 mg/kg (rabbit)
Dermal	LD50	>20000 mg/kg (rabbit)
Inhalative	LC50/4 h	29.3 mg/l (rat)
· Primary ir		
		ation Based on available data, the classification criteria are not met.
· Serious e		
Causes se		
		sensitisation Based on available data, the classification criteria are not met.
 Germ cell Not applica 		icity
		lata, the classification criteria are not met.
		sed on available data, the classification criteria are not met.
		ity Based on available data, the classification criteria are not met.
		ure May cause drowsiness or dizziness.
STOT-rep	eated exp	osure Based on available data, the classification criteria are not met.
		Based on available data, the classification criteria are not met.
		gical information:
		e toxicity, irritation and corrosivity) Not applicable.
· Sensitisat		
		i city Not applicable. • other hazards
-		
	-	ng properties
None of th	e ingredie	nts is listed.
SECTIO	N 12: Ec	ological information
· 12.1 Toxic	city	
		o further relevant information available.
		nd degradability No further relevant information available.
		ve potential No further relevant information available.
		No further relevant information available.
		Γ and vPvB assessment
• PBT: Not a		
· vPvB: Not		
	crine aisi	rupting properties

The product does not contain substances with endocrine disrupting properties.

- 12.7 Other adverse effects
- · Additional ecological information:
- · General notes:

Do not allow undiluted product or large quantities of it to reach ground water, water course or sewage system.

(Contd. on page 10)



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

(Contd. of page 9)

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

· Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

Disposal must be made according to official regulations.

· European waste catalogue

08 04 09* w

waste adhesives and sealants containing organic solvents or other hazardous substances

· Uncleaned packaging:

Recommendation:

Packagings that may not be cleansed are to be disposed of in the same manner as the product.

SECTION 14: Transport information	
 14.1 UN number or ID number ADR/ADN, IMDG, IATA 	UN1133
 14.2 UN proper shipping name ADR/ADN IMDG, IATA 	1133 ADHESIVES ADHESIVES
• 14.3 Transport hazard class(es) • ADR/ADN	
· Class · Label	3 (F1) Flammable liquids. 3
· Class · Label	3 Flammable liquids. 3
· 14.4 Packing group · ADR/ADN, IMDG, IATA	111
 14.5 Environmental hazards: Marine pollutant: 	No
 14.6 Special precautions for user Hazard identification number (Kemler code): EMS Number: 	Warning: Flammable liquids. - F-E,S-D
	(Contd. on page 11)



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

	(Contd. of page 10
· Stowage Category	A
 14.7 Maritime transport in bulk according to IMO instruments 	Not applicable.
 Transport/Additional information: Quantity limitations 	On passenger aircraft/rail: 60 L On cargo aircraft only: 220 L
 ADR/ADN Limited quantities (LQ) Excepted quantities (EQ) 	5L Code: E1 Maximum net quantity per inner packaging: 30 ml Maximum net quantity per outer packaging: 1000
 Transport category Tunnel restriction code 	ml 3 E
 IMDG Limited quantities (LQ) Excepted quantities (EQ) Remarks: 	5L Code: E1 Maximum net quantity per inner packaging: 30 ml Maximum net quantity per outer packaging: 1000 ml For substances with class 3 according to IMDG
· UN "Model Regulation":	Code chapter 2.3.2.2 packing group is classified in packing group III, as viscosity is in accordance with requirements (flow time t > 100s).

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- · Seveso category P5c FLAMMABLE LIQUIDS
- \cdot Qualifying quantity (tonnes) for the application of lower-tier requirements $5000\ t$
- Qualifying quantity (tonnes) for the application of upper-tier requirements 50000 t
- REGULATION (EC) No 1907/2006 ANNEX XVII Conditions of restriction: 3
- DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment Annex II
 None of the ingredients is listed.
- · REGULATION (EU) 2019/1148
- · Regulation (EC) No 273/2004 on drug precursors

67-64-1 Acetone

(Contd. on page 12)

3

EU -



Printing date 19.03.2025

Version number 40 (replaces version 39)

Revision: 17.12.2024

Trade name: GRF SUPERTRASPARENTE TI 5L*1 L616

(Contd. of page 11)

3

 Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors

67-64-1 Acetone

15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

for any specific product features and shall not e	edge. However, this shall not constitute a guarantee stablish a legally valid contractual relationship.
Relevant phrasesH225Highly flammable liquid and vapour.H317May cause an allergic skin reaction.H319Causes serious eye irritation.H336May cause drowsiness or dizziness.H361fSuspected of damaging fertility.H400Very toxic to aquatic life.H410Very toxic to aquatic life with long lastiEUH066Repeated exposure may cause skin di	ryness or cracking.
Classification according to Regulation (EC)	
Serious eye damage/irritation Specific target organ toxicity (single exposure)	Bridging principles The classification of the mixture is generally based on the calculation method using substance data according to Regulation (EC) No 1272/2008.
 Date of previous version: 12.02.2024 Version number of previous version: 39 Abbreviations and acronyms: ADR: Accord relatif au transport international des marchar the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and La EINECS: European Inventory of Existing Commercial Chem ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American 	nical Substances