

Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

SECTION 1: Identification of the substance/mixture and of the company/ undertaking

1.1 Product identifier

• Trade name: BIS PU MAX TR CQ 340G*12 L106

- **1.2 Relevant identified uses of the substance or mixture and uses advised against** No further relevant information available.
- · Application of the substance / the mixture Adhesive

1.3 Details of the supplier of the safety data sheet Manufacturer/Supplier: Bison International Dr.A.F.Philipsstraat 9 NL-4462 EW Goes PO Box 160 NL-4460 AD Goes tel. +31 88 3235700 fax. +31 88 3235800 e mail: sds@boltonadhesives.com Further information obtainable from: Bison QESH

• **1.4 Emergency telephone number:** Members of the public seeking specific information on poisons should contact: In England and Wales: NHS 111 - dial 111 In Scotland: NHS 24 - dial 111

SECTION 2: Hazards identification

• 2.1 Classification of the substance or mixture

Classification according to Regulation (EC) No 1272/2008

GHS08 health hazard

Resp. Sens. 1	H334 May cause allergy or asthma symptoms or breathing difficulties if inhaled.
Carc. 2	H351 Suspected of causing cancer.
STOT RE 2	H373 May cause damage to organs through prolonged or repeated exposure.

 $\boldsymbol{\wedge}$

🔀 GHS09 environment

Aquatic Chronic 2 H411 Toxic to aquatic life with long lasting effects.



Acute Tox. 4	H332 Harmful if inhaled.
Skin Irrit. 2	H315 Causes skin irritation.
Eye Irrit. 2	H319 Causes serious eye irritation.
Skin Sens. 1	H317 May cause an allergic skin reaction.

STOT SE 3 H335 May cause respiratory irritation.

(Contd. on page 2) GB-EN



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

Trade name: BIS PU MAX TR CQ 340G*12 L106

	(Contd. of page 1
2.2 Label elements	
Labelling according to Regulation (EC) No 1272/2008	
The product is classified and labelled according to the GB CLP regulation.	
Hazard pictograms	
\vee \vee \vee	
GHS07 GHS08 GHS09	
Signal word Danger	
Hazard-determining components of labelling:	
Aromatic polyisocyanate based prepolymer	
4,4'-methylenediphenyl diisocyanate	
o-(p-isocyanatobenzyl)phenyl isocyanate	
Hazard statements	
H332 Harmful if inhaled.	
H315 Causes skin irritation.	
H319 Causes serious eye irritation.	
H334 May cause allergy or asthma symptoms or breathing difficulties if inhaled.	
H317 May cause an allergic skin reaction.	
H351 Suspected of causing cancer.	
H335 May cause respiratory irritation.	
H373 May cause damage to organs through prolonged or repeated exposure.	
H411 Toxic to aquatic life with long lasting effects.	
Precautionary statements	
P101 If medical advice is needed, have product container or label at hand.	
P102 Keep out of reach of children.	
P260 Do not breathe vapours.	
P280 Wear protective gloves/protective clothing/eye protection/face protectio	
P342+P311 If experiencing respiratory symptoms: Call a POISON CENTER/doctor.	
P403+P233 Store in a well-ventilated place. Keep container tightly closed.	
P501 Dispose of contents/container in accordance with national regulations.	
Additional information:	
EUH204 Contains isocyanates. May produce an allergic reaction.	
As from 24 August 2023 adequate training is required before industrial or profession	nal use.
2.3 Other hazards	
Results of PBT and vPvB assessment	
PBT: Not applicable.	
vPvB: Not applicable.	
SECTION 3: Composition/information on ingredients	

· 3.2 Mixtures

· **Description:** Adhesive

· Dangerous components:

CAS: 99784-49-3

Aromatic polyisocyanate based prepolymer Resp. Sens. 1, H334; STOT RE 2, H373; O Acute Tox. 4, H332; Skin Irrit. 2, H315; Eye Irrit. 2, H319; Skin Sens. 1, H317; STOT SE 3, H335

50-100%

(Contd. on page 3)

- GB-EN



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

Trade name: BIS PU MAX TR CQ 340G*12 L106

(Contd. of page 2)					
CAS: 101-68-8 4,4'-methylenediphenyl diisocyanate					
EINECS: 202-966-0					
Index number: 615-005-00-9	H373; 🗄 Acute Tox. 4, H332; Skin Irrit. 2, H315; Eye Irrit.				
Reg.nr.: 01-2119457014-47	2, H319, Skin Sens. 1, H317; STOT SE 3, H335, EUH204				
	Specific concentration limits:				
	Skin Irrit. 2; H315: C ≥ 5 %				
	Eye Irrit. 2; H319: C ≥ 5 %				
	Resp. Sens. 1; H334: C ≥ 0.1 %				
	STOT SE 3; H335: C ≥ 5 %				
CAS: 5873-54-1	CAS: 5873-54-1 o-(p-isocyanatobenzyl)phenyl isocyanate 10-25%				
EINECS: 227-534-9	EINECS: 227-534-9 🚯 Resp. Sens. 1, H334; Carc. 2, H351; STOT RE 2,				
Index number: 615-005-00-9	EINECS: 227-534-9 Index number: 615-005-00-9 H373; Acute Tox. 4, H332; Skin Irrit. 2, H315; Eye Irrit.				
Reg.nr.: 01-2119480143-45	Reg.nr.: 01-2119480143-45 2, H319; Skin Sens. 1, H317; STOT SE 3, H335, EUH204				
	Specific concentration limits:				
	Skin Irrit. 2; H315: C ≥ 5 %				
	Eye Irrit. 2; H319: C ≥ 5 %				
	Resp. Sens. 1; H334: C ≥ 0.1 %				
	STOT SE 3; H335: C ≥ 5 %				
· Additional information: For	Additional information: For the wording of the listed hazard phrases refer to section 16.				

SECTION 4: First aid measures

· 4.1 Description of first aid measures

General information:

Symptoms of poisoning may even occur after several hours; therefore medical observation for at least 48 hours after the accident.

· After inhalation:

Supply fresh air and to be sure call for a doctor.

- In case of unconsciousness place patient stably in side position for transportation.
- · After skin contact: Immediately wash with water and soap and rinse thoroughly.
- After eye contact:
- Rinse opened eye for several minutes under running water. If symptoms persist, consult a doctor.
- After swallowing: If symptoms persist consult doctor.
- **4.2 Most important symptoms and effects, both acute and delayed** No further relevant information available.
- **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

SECTION 5: Firefighting measures

· 5.1 Extinguishing media

• Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.

- 5.2 Special hazards arising from the substance or mixture
- During heating or in case of fire poisonous gases are produced.
- · 5.3 Advice for firefighters
- · Protective equipment: Mouth respiratory protective device.

(Contd. on page 4)



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

Trade name: BIS PU MAX TR CQ 340G*12 L106

(Contd. of page 3)

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Mount respiratory protective device.
- 6.2 Environmental precautions: Inform respective authorities in case of seepage into water course or sewage system. Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up: Send for recovery or disposal in suitable receptacles. Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust). Dispose contaminated material as waste according to item 13. Ensure adequate ventilation.
- 6.4 Reference to other sections
 See Section 7 for information on safe handling.
 See Section 8 for information on personal protection equipment.
 See Section 13 for disposal information.

SECTION 7: Handling and storage

· 7.1 Precautions for safe handling

Ensure good ventilation/exhaustion at the workplace. Prevent formation of aerosols.

· Information about fire - and explosion protection: Keep respiratory protective device available.

- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage:

· Requirements to be met by storerooms and receptacles: No special requirements.

· Information about storage in one common storage facility: Not required.

- · Further information about storage conditions: Keep container tightly sealed.
- Storage class: 10
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· 8.1 Control parameters

· Ingredients with limit values that require monitoring at the workplace:

101-68-8 4,4'-methylenediphenyl diisocyanate

WEL Short-term value: 0.07 mg/m³ Long-term value: 0.02 mg/m³ Sen; as -NCO

5873-54-1 o-(p-isocyanatobenzyl)phenyl isocyanate

WEL Short-term value: 0.07 mg/m³ Long-term value: 0.02 mg/m³

Sen; as -NCO

(Contd. on page 5)



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

Trade name: BIS PU MAX TR CQ 340G*12 L106

101-68-8 4,4'-methylenediphenyl diisocyanate BMGV 1 µmol creatinine/mol Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine 5873-54-1 o-(p-isocyanatobenzyl)phenyl isocyanate BMGV 1 µmol creatinine/mol Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Work Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Work Tightly sealed goggles	Inared	(Contd. of page 4
BMGV 1 µmol creatinine/mol Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine 5873-54-1 o-(p-isocyanatobenzyl)phenyl isocyanate BMGV 1 µmol creatinine/mol Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection Respiratory protection Not required. Hand protection Not required. Hand protection Not required. Hand protection Not required. Mediadion. Recenterial has to be impermeable and resistant to the product/ the substance/ preparation.	-	-
Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine 5873-54-1 o-(p-isocyanatobenzyl)phenyl isocyanate BMGV 1 proof creatinine/mol Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective masures, such as personal protective equipment General protective masures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Tightly sealed goggles		
Parameter: isocyanate-derived diamine 5873-54-1 o-(p-isocyanatobenzyl)phenyl isocyanate BMGV 1 µmol creatinine/mol Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection WW Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Wirthy value gasels Tightly sealed goggles		
5873-54-1 o-(p-isocyanatobenzyl)phenyl isocyanate BMGV 1 µmol creatinine/mol Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual protection measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Wash and skin. Respiratory protection: Not required. Hand protection Hand protection Section of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time for the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Tightly		
BMGV 1 µmol creatinine/mol Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection View Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ Preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetrati		
Medium: urine Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. S.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / times / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protective gloves Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material Perfection Conterion Vitrile rubber, NBR Penetration time has to be at least 10 minu Perfection Sittle perfection The mixture of chemicals mentioned below the penetration time has to be at least 10 minu Perfecti		
Sampling time: At the end of the period od exposure Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Motion Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the gloves material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Eye/face protection Tightly sealed goggles	BMGV	
Parameter: isocyanate-derived diamine Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Vivo Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Vipel/face protection <th></th> <td></td>		
Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / furmes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
 8.2 Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles	Additic	·
Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protective Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection		
Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Protective gloves Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
The usual precautionary measures are to be adhered to when handling chemicals. Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection : Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection		
Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection : Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Wash hands before breaks and at the end of work. Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles	Keep a	way from foodstuffs, beverages and feed.
Store protective clothing separately. Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Do not inhale gases / fumes / aerosols. Avoid contact with the eyes and skin. Respiratory protection : Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Avoid contact with the eyes and skin. Respiratory protection: Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Respiratory protection: Not required. Hand protection Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Hand protection Image: Protective gloves The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles	ന്ന	
The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles	1112	Protective gloves
preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles	L	
preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles	The al	ove material has to be impermeable and resistant to the product/ the substance/ th
degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
(Permeation according to EN 374 Part 3: Level 1). Eye/face protection Tightly sealed goggles		
Eye/face protection Tightly sealed goggles		
		Tightly sealed goggles
	$\mathbf{\nabla}$	
Goggles recommended during refilling	Gogale	es recommended during refilling
	Joggie	(Contd. on page 6



Safety data sheet according to 1907/2006/EC, Article 31

Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

(Contd. of page 5)

Trade name: BIS PU MAX TR CQ 340G*12 L106

· Body protection: Use protective suit.

SECTION 9: Physical and chemical properties		
· 9.1 Information on basic physical and chemical properties		
General Information		
· Physical state	Fluid	
· Colour:	Light brown	
· Odour:	Characteristic	
· Odour threshold:	Not determined.	
 Melting point/freezing point: 	Undetermined.	
 Boiling point or initial boiling point and 		
boiling range	208 °C	
· Flammability	Not applicable.	
Lower and upper explosion limit		
· Lower:	0.4 Vol %	
· Upper:	0.0 Vol %	
· Flash point:	201 °C	
Ignition temperature:	520 °C	
Decomposition temperature:	Not determined.	
· pH	Not determined.	
· Viscosity:		
· Kinematic viscosity	Not determined.	
· Dynamic:	Not determined.	
Solubility	Not determined.	
· water:	Not miscible or difficult to mix.	
Partition coefficient n-octanol/water (log		
	Not determined.	
value)	0 hPa	
· Vapour pressure at 20 °C:	0 nPa	
Density and/or relative density	1 1 1 6 1 / 2	
Density at 20 °C:	1.146 g/cm ³	
• Relative density	Not determined.	
· Vapour density	Not determined.	
• 9.2 Other information	All relevant physical data were determined for the	
	mixture. All non-determined data are not	
	measurable or not relevant for the	
	characterization of the mixture.	
· Appearance:		
Form:	Liquid	
Important information on protection of hea		
and environment, and on safety.		
· Auto-ignition temperature:	Product is not selfigniting.	
· Explosive properties:	Product does not present an explosion hazard.	
· Solvent content:		
· Solids content:	96.7 %	
· Change in condition	00.1 /0	
· Evaporation rate	Not determined.	
	(Contd. on page 7)	



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

Trade name: BIS PU MAX TR CQ 340G*12 L106

		(Contd. of page
Information with regard to physical haz	ard	
classes		
Explosives	Void	
Flammable gases	Void	
Aerosols	Void	
Oxidising gases	Void	
Gases under pressure	Void	
Flammable liquids	Void	
Flammable solids	Void	
Self-reactive substances and mixtures	Void	
Pyrophoric liquids	Void	
Pyrophoric solids	Void	
Self-heating substances and mixtures	Void	
Substances and mixtures, which emit		
flammable gases in contact with water	Void	
Oxidising liquids	Void	
Oxidising solids	Void	
Organic peroxides	Void	
Corrosive to metals	Void	
Desensitised explosives	Void	

SECTION 10: Stability and reactivity

· 10.1 Reactivity No further relevant information available.

· 10.2 Chemical stability

• Thermal decomposition / conditions to be avoided:

No decomposition if used according to specifications.

· 10.3 Possibility of hazardous reactions

Reacts with alcohols.

Reacts with water.

Reacts with alkali, amines and strong acids.

• **10.4 Conditions to avoid** No further relevant information available.

• 10.5 Incompatible materials: No further relevant information available.

• 10.6 Hazardous decomposition products: Danger of forming toxic pyrolysis products.

SECTION 11: Toxicological information

• 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008 • Acute toxicity Harmful if inhaled.

· LD/LC50 values relevant for classification:

101-68-8 4,4'-methylenediphenyl diisocyanate

Oral LD50 2200 mg/kg (mouse)

Skin corrosion/irritation

Causes skin irritation.

· Serious eye damage/irritation

Causes serious eye irritation.

(Contd. on page 8)



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

(Contd. of page 7)

Trade name: BIS PU MAX TR CQ 340G*12 L106

· Respiratory or skin sensitisation

May cause allergy or asthma symptoms or breathing difficulties if inhaled.

May cause an allergic skin reaction.

Germ cell mutagenicity

Not applicable.

Based on available data, the classification criteria are not met.

- · Carcinogenicity Suspected of causing cancer.
- · Reproductive toxicity Based on available data, the classification criteria are not met.
- · STOT-single exposure May cause respiratory irritation.
- STOT-repeated exposure May cause damage to organs through prolonged or repeated exposure.
- Aspiration hazard Based on available data, the classification criteria are not met.
- · Additional toxicological information:
- Acute effects (acute toxicity, irritation and corrosivity) Not applicable.
- · Sensitisation Not applicable.
- · Repeated dose toxicity Not applicable.
- · 11.2 Information on other hazards

· Endocrine disrupting properties

None of the ingredients is listed.

SECTION 12: Ecological information

- · 12.1 Toxicity
- · Aquatic toxicity: No further relevant information available.
- **12.2 Persistence and degradability** No further relevant information available.
- **12.3 Bioaccumulative potential** No further relevant information available.
- · 12.4 Mobility in soil No further relevant information available.
- · 12.5 Results of PBT and vPvB assessment
- · PBT: Not applicable.
- vPvB: Not applicable.
- 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

- · 12.7 Other adverse effects
- · Remark: Toxic for fish
- · Additional ecological information:
- · General notes:

Water hazard class 1 (German Regulation) (Self-assessment): slightly hazardous for water Do not allow undiluted product or large quantities of it to reach ground water, water course or sewage system.

Also poisonous for fish and plankton in water bodies.

Toxic for aquatic organisms

SECTION 13: Disposal considerations

13.1 Waste treatment methods

· Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

Disposal must be made according to official regulations.

(Contd. on page 9)



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

(Contd. of page 8)

Trade name: BIS PU MAX TR CQ 340G*12 L106

· Uncleaned packaging:

Recommendation:

Packagings that may not be cleansed are to be disposed of in the same manner as the product.

SECTION 14: Transport informa	tion
 14.1 UN number or ID number ADR/ADN, IMDG, IATA 	UN3082
 14.2 UN proper shipping name ADR/ADN IMDG, IATA 	3082 ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (o-(p- isocyanatobenzyl)phenyl isocyanate, 4,4'- methylenediphenyl diisocyanate) ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (o-(p- isocyanatobenzyl)phenyl isocyanate, 4,4'- methylenediphenyl diisocyanate)
• 14.3 Transport hazard class(es)	
ADR/ADN	
Class	9 (M6) Miscellaneous dangerous substances and articles.
· Label	9
· Class	9 Miscellaneous dangerous substances and articles.
	9
· Class	9 Miscellaneous dangerous substances and articles.
·Label	9
 14.4 Packing group ADR/ADN, IMDG, IATA 	III
	(Contd. on page 10) GB-E



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

Trade name: BIS PU MAX TR CQ 340G*12 L106

	(Contd. of page
 14.5 Environmental hazards: Marine pollutant: Special marking (ADR/ADN): Special marking (IATA): 	No Symbol (fish and tree) Symbol (fish and tree)
· 14.6 Special precautions for user	Warning: Miscellaneous dangerous substances
 Hazard identification number (Kemler code): EMS Number: Stowage Category 	and articles. 90 F-A,S-F A
 14.7 Maritime transport in bulk according to IMO instruments 	Not applicable.
 Transport/Additional information: Quantity limitations 	On passenger aircraft/rail: 450 L On cargo aircraft only: 450 L
 ADR/ADN Limited quantities (LQ) Excepted quantities (EQ) 	5L Code: E1 Maximum net quantity per inner packaging: 30 ml Maximum net quantity per outer packaging: 100 ml
 Transport category Tunnel restriction code 	3 (-)
 IMDG Limited quantities (LQ) Excepted quantities (EQ) 	5L Code: E1 Maximum net quantity per inner packaging: 30 ml Maximum net quantity per outer packaging: 1000 ml
· Remarks:	Under certain conditions substances in Class (flammable liquids) can be classified i packinggroup III. See IMDG, Part 2, Chapter 2.3, Paragraph 2.3.2.2
· UN "Model Regulation":	UN 3082 ENVIRONMENTALLY HAZARDOU SUBSTANCE, LIQUID, N.O.S. (O-(P ISOCYANATOBENZYL)PHENYL ISOCYANATE 4,4'-METHYLENEDIPHENYL DIISOCYANATE 9, III

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- Seveso category E2 Hazardous to the Aquatic Environment

(Contd. on page 11)



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

Trade name: BIS PU MAX TR CQ 340G*12 L106

(Contd. of page 10)

· Qualifying quantity (tonnes) for the application of lower-tier requirements 200 t · Qualifying quantity (tonnes) for the application of upper-tier requirements 500 t

- REGULATION (EC) No 1907/2006 ANNEX XVII Conditions of restriction: 3, 56a, 56b, 74
- · DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment – Annex II

None of the ingredients is listed.

· REGULATION (EU) 2019/1148

Annex I - RESTRICTED EXPLOSIVES PRECURSORS (Upper limit value for the purpose of licensing under Article 5(3))

None of the ingredients is listed.

Annex II - REPORTABLE EXPLOSIVES PRECURSORS

None of the ingredients is listed.

Regulation (EC) No 273/2004 on drug precursors

None of the ingredients is listed.

Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors

None of the ingredients is listed.

• 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

Relevant phrases

- H315 Causes skin irritation.
- H317 May cause an allergic skin reaction.
- Causes serious eye irritation. H319
- H332 Harmful if inhaled.
- H334 May cause allergy or asthma symptoms or breathing difficulties if inhaled.

H335 May cause respiratory irritation.

H351 Suspected of causing cancer.

H373 May cause damage to organs through prolonged or repeated exposure.

EUH204 Contains isocyanates. May produce an allergic reaction.		
 Classification according to Regulation (EC) No 1272/2008 		
Acute toxicity - inhalation Skin corrosion/irritation Serious eye damage/irritation Respiratory sensitisation Skin sensitisation Carcinogenicity Specific target organ toxicity (single exposure) Specific target organ toxicity (repeated exposure) Hazardous to the aquatic environment - long- term (chronic) aquatic hazard	The classification of the mixture is generally based on the calculation method using substance data according to Regulation (EC) No 1272/2008.	
• Department issuing SDS: Bison QESH		

(Contd. on page 12) GB-EN



Printing date 03.08.2023

Version number 37 (replaces version 36)

Revision: 03.08.2023

Trade name: BIS PU MAX TR CQ 340G*12 L106

(Con	td. of page 11)
· Contact: Reach coordinator	
· Date of previous version: 03.02.2023	
Version number of previous version: 36	
· Abbreviations and acronyms:	
ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreeme	nt Concernina
the International Carriage of Dangerous Goods by Road)	g
IMDG: International Maritime Code for Dangerous Goods	
IATA: International Air Transport Association	
GHS: Globally Harmonised System of Classification and Labelling of Chemicals	
EINECS: European Inventory of Existing Commercial Chemical Substances	
ELINCS: European List of Notified Chemical Substances	
CAS: Chemical Abstracts Service (division of the American Chemical Society)	
LC50: Lethal concentration, 50 percent	
LD50: Lethal dose, 50 percent	
PBT: Persistent, Bioaccumulative and Toxic	
vPvB: very Persistent and very Bioaccumulative	
Acute Tox. 4: Acute toxicity – Category 4	
Skin Irrit. 2: Skin corrosion/irritation – Category 2	
Eye Irrit. 2: Serious eye damage/eye irritation – Category 2	
Resp. Sens. 1: Respiratory sensitisation – Category 1	
Skin Sens. 1: Skin sensitisation – Category 1	
Carc. 2: Carcinogenicity – Category 2	
STOT SE 3: Specific target organ toxicity (single exposure) – Category 3	
STOT RE 2: Specific target organ toxicity (repeated exposure) – Category 2	
Aquatic Chronic 2: Hazardous to the aquatic environment - long-term aquatic hazard – Category 2	
• * Data compared to the previous version altered.	
	GB-E