

Printing date 22.03.2025 Versi

Version number 37 (replaces version 36)

Revision: 22.03.2025

SECTION 1: Identification of the substance/mixture and of the company/ undertaking

· 1.1 Product identifier

- · Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT
- **1.2 Relevant identified uses of the substance or mixture and uses advised against** No further relevant information available.
- · Application of the substance / the mixture Adhesive

• 1.3 Details of the supplier of the safety data sheet • Manufacturer/Supplier:

Bison International Dr.A.F.Philipsstraat 9 NL-4462 EW Goes PO Box 160 NL-4460 AD Goes tel. +31 88 3235700 fax. +31 88 3235800 e mail: sds@boltonadhesives.com

· Further information obtainable from: PSRA

· 1.4 Emergency telephone number:

Bison and Griffon products: +31 88 3235700. Operating hours mo-fr 08:00h-17:00h (CET) UHU products: + 49 (0) 30/19240 (Notruf). Operating hours mo-fr 08:00h-17:00h (CET)

For detailed information contact the national Poison Centre @ https://poisoncentres.echa.europa.eu/appointed-bodies

SECTION 2: Hazards identification

· 2.1 Classification of the substance or mixture

Classification according to Regulation (EC) No 1272/2008

The product is not classified, according to the CLP regulation.

- · 2.2 Label elements
- · Labelling according to Regulation (EC) No 1272/2008 Void
- · Hazard pictograms Void
- · Signal word Void
- Hazard statements Void
- Additional information:
- EUH208 Contains mixture of 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1), 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction.
- EUH210 Safety data sheet available on request.
- · 2.3 Other hazards
- · Results of PBT and vPvB assessment
- · **PBT:** Not applicable.
- vPvB: Not applicable.

SECTION 3: Composition/information on ingredients

- · 3.2 Mixtures
- · Description: Adhesive

(Contd. on page 2)

EU -



Printing date 22.03.2025

Version number 37 (replaces version 36)

Revision: 22.03.2025

Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT

(Contd. of page 1) · Dangerous components: CAS: 2634-33-5 1,2-benzisothiazol-3(2H)-one <0.025% EINECS: 220-120-9 Eye Dam. 1, H318; 🥸 Aquatic Acute 1, H400; Aquatic Chronic 1, H410; 🕥 Acute Index number: 613-088-00-6 Reg.nr.: 01-2120761540-60-Tox. 4, H302; Skin Irrit. 2, H315; Škin Sens. XXXX 1, H317 Specific concentration limit: Skin Sens. 1;H317: C ≥ 0.05 % CAS: 55965-84-9 mixture of 5-chloro-2-methyl-2H-isothiazol- ≥0.00025-<0.0015% 3-one [EC no. 247-500-7] and 2-methyl-2H-Index number: 613-167-00-5 isothiazol-3-one [EC no. 220-239-6] (3:1) Reg.nr.: 01-2120764691-48-Acute Tox. 3, H301; Acute Tox. 2, H310; Acute Tox. 2, H330; XXXX 1C, H314; Eye Dam. 1, H318; 🚯 Aquatic Acute 1, H400 (M=100); Aquatic Chronic 1, H410 (M=100); 🔿 Skin Sens. 1A, H317, EUH071 Specific concentration limits: Skin Corr. 1C;H314: C ≥ 0.6 % Skin Irrit. 2; H315: 0.06 % ≤ C < 0.6 % Eye Dam. 1; H318: C ≥ 0.6 % Eye Irrit. 2; H319: 0.06 % ≤ C < 0.6 % Skin Sens. 1A; H317: C ≥ 0.0015 % • Additional information: For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

- · 4.1 Description of first aid measures
- · General information: No special measures required.
- After inhalation:
- Supply fresh air; consult doctor in case of complaints.
- No special measures required.
- · After skin contact: Generally the product does not irritate the skin.
- After eye contact: Rinse opened eye for several minutes under running water.
- · After swallowing: If symptoms persist consult doctor.
- 4.2 Most important symptoms and effects, both acute and delayed
- No further relevant information available.
- 4.3 Indication of any immediate medical attention and special treatment needed

No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.
- **5.2 Special hazards arising from the substance or mixture** No further relevant information available.

(Contd. on page 3)



Printing date 22.03.2025

Version number 37 (replaces version 36)

Revision: 22.03.2025

(Contd. of page 2)

Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT

• 5.3 Advice for firefighters

· Protective equipment: No special measures required.

SECTION 6: Accidental release measures

- · 6.1 Personal precautions, protective equipment and emergency procedures Not required.
- · 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up: Send for recovery or disposal in suitable receptacles.
- Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).
- 6.4 Reference to other sections
- No dangerous substances are released.
- See Section 7 for information on safe handling.
- See Section 8 for information on personal protection equipment.
- See Section 13 for disposal information.

SECTION 7: Handling and storage

• 7.1 Precautions for safe handling No special precautions are necessary if used correctly.

- · Information about fire and explosion protection: No special measures required.
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage:

· Requirements to be met by storerooms and receptacles: No special requirements.

- · Information about storage in one common storage facility: Not required.
- Further information about storage conditions: None.
- · Storage class: 12
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· 8.1 Control parameters

· Ingredients with limit values that require monitoring at the workplace:

The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace.

· DNELs

Dermal	Worker, dermal, longterm exposition		0.966 mg/kg bw/day	
	Consumer, dermal, longterm exposition		0.345 mg/kg bw/day	
Inhalative Worker, inha		lative, longterm exposition	6.81 mg/m³	
	Consumer, inhalative, longterm exposition		1.2 mg/m³	
PNECs				
2634-33-5	1,2-benzisot	hiazol-3(2H)-one		
Fresh water		0.00403 mg/l		
Fresh water sediment		0.0499 mg/kg dry weight		
Marine water		0.000403 mg/l		
		•		(Contd. on page



Printing date 22.03.2025

Version number 37 (replaces version 36)

Revision: 22.03.2025

Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT

Marine sediment 0.00499 mg/kg dry weight Soil 3 mg/kg Sewage treatment plant 1.03 mg/l 55965-84-9 mixture of 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2- methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) Fresh water 0.00339 mg/l Karine sediment 0.027 mg/kg dry weight Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR	Marina andina ant	(Contd. of page 3)				
Sewage treatment plant 1.03 mg/l 55965-84-9 mixture of 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) Fresh water 0.00339 mg/l Fresh water sediment 0.027 mg/kg dry weight Marine water 0.00339 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.027 mg/kg dry weight Soil 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the materia	iviarine segiment	0.00499 mg/kg dry weight				
55965-84-9 mixture of 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) Fresh water 0.00339 mg/l Fresh water sediment 0.027 mg/kg dry weight Marine water 0.00339 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Matriel of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN						
methyl-2H-isothiazol-3-one [ÉC no. 220-239-6] (3:1) Fresh water 0.00339 mg/l Fresh water sediment 0.027 mg/kg dry weight Marine water 0.0039 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).						
Fresh water sediment 0.027 mg/kg dry weight Marine water 0.00339 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. Az Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).						
Marine water 0.00339 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Fresh water	0.00339 mg/l				
Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Fresh water sediment	0.027 mg/kg dry weight				
Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Marine water	0.00339 mg/l				
Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Marine sediment	0.027 mg/kg dry weight				
Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Soil	0.01 mg/kg				
 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1). 	Sewage treatment plant	0.23 mg/l				
 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1). 	-					
	preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).					
	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go	ss of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1).				
	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on bas	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties				
• General Information • Physical state Fluid	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of cherr (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on bas General Information	as of the material: > 0,12 mm ove material hicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). byggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid				
General Information Physical state Fluid Colour: According to product specification	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of cherr (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on bas General Information Physical state Colour:	as of the material: > 0,12 mm ove material hicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). byggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid According to product specification				
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of cherr (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on bas General Information Physical state Colour: Odour:	as of the material: > 0,12 mm ove material hicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). byggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid According to product specification Characteristic				
• Colour: According to product specification • Odour: Characteristic • Odour threshold: Not determined.	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of cherr (Permeation according to Eye/face protection Go SECTION 9: Physical 9.1 Information on bas General Information Physical state Colour: Odour: Odour threshold:	as of the material: > 0,12 mm ove material hicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid According to product specification Characteristic Not determined.				
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined.	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of cherr (Permeation according to Eye/face protection Go SECTION 9: Physica 9.1 Information on bas General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing	as of the material: > 0,12 mm ove material hicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid According to product specification Characteristic Not determined. point: Undetermined.				
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and Fuid	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physical SECTION 9: Physical General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing Boiling point or initial	as of the material: > 0,12 mm ove material hicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). biggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid According to product specification Characteristic Not determined. Undetermined.				
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and boiling range 100 °C	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physical SECTION 9: Physical General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing Boiling point or initial boiling range	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid According to product specification Characteristic Not determined. point: boiling point and 100 °C				
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and boiling range 100 °C Flammability Not applicable.	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physical SECTION 9: Physical Second State Colour: Odour: Odour: Odour threshold: Melting point/freezing Boiling point or initial boiling range Flammability	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid According to product specification Characteristic Not determined. point: boiling point and 100 °C Not applicable.				
General InformationFluidPhysical stateFluidColour:According to product specificationOdour:CharacteristicOdour threshold:Not determined.Melting point/freezing point:Undetermined.Boiling point or initial boiling point and boiling range100 °C	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of cherr (Permeation according to Eye/face protection Go SECTION 9: Physica 9.1 Information on bas General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing Boiling point or initial boiling range Flammability Lower and upper explored	as of the material: > 0,12 mm by ematerial hicals mentioned below the penetration time has to be at least 10 minutes o EN 374 Part 3: Level 1). by ggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid According to product specification Characteristic Not determined. boiling point and 100 °C Not applicable.				



Printing date 22.03.2025

Version number 37 (replaces version 36)

Revision: 22.03.2025

Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT

	(Contd. of page
Upper:	Not determined.
Flash point:	Not applicable.
Decomposition temperature:	Not determined.
pH at 20 °C	5
Viscosity:	
Kinematic viscosity	Not determined.
Dynamic:	Not determined.
Solubility	
water:	Not miscible or difficult to mix.
Partition coefficient n-octanol/water (log	
value)	Not determined.
Vapour pressure at 20 °C:	23 hPa
Density and/or relative density	
Density at 20 °C:	1.12 g/cm³
Relative density	Not determined.
Vapour density	Not determined.
• •	
9.2 Other information	All relevant physical data were determined for th mixture. All non-determined data are no
	measurable or not relevant for th
A	characterization of the mixture.
Appearance:	Fluid
Form:	Fluid
Important information on protection of heal	in state of the st
and environment, and on safety.	Due durat in mat a alfimation
Ignition temperature:	Product is not selfigniting.
Explosive properties:	Product does not present an explosion hazard.
Solvent content:	40.4.9/
Water:	40.1 %
VOC (EC)	0.00 %
Solids content:	60.0 %
Change in condition	
Evaporation rate	Not determined.
Information with regard to physical haza	rd
classes	
Explosives	Void
Flammable gases	Void
Aerosols	Void
Oxidising gases	Void
Gases under pressure	Void
Flammable liquids	Void
	Void
Flammable solids	
	Void
Self-reactive substances and mixtures	Void Void
Self-reactive substances and mixtures Pyrophoric liquids	
Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids	Void
Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit	Void Void
Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit	Void Void Void
Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water	Void Void Void
Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit	Void Void Void



Printing date 22.03.2025

Version number 37 (replaces version 36)

Revision: 22.03.2025

(Contd. of page 5)

Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT

Organic peroxides
 Corrosive to metals
 Desensitised explosives

Void Void Void

SECTION 10: Stability and reactivity

· 10.1 Reactivity No further relevant information available.

· 10.2 Chemical stability

Thermal decomposition / conditions to be avoided:

No decomposition if used according to specifications.

- 10.3 Possibility of hazardous reactions No dangerous reactions known.
- **10.4 Conditions to avoid** No further relevant information available.
- · 10.5 Incompatible materials: No further relevant information available.
- 10.6 Hazardous decomposition products: No dangerous decomposition products known.

SECTION 11: Toxicological information

· LD/LC50 values relevant for classification:				
2634-33-5 1,2-benzisothiazol-3(2H)-one				
Oral	LD50	670 mg/kg (rat)		
Dermal	LD50	>2000 mg/kg (rat)		
Inhalative	LC50/4 h	0.4 mg/l (rat)		
 Serious e Respirato Germ cell Not applic Based on Carcinoge Reproduce 	osion/irrita ye damag ry or skin mutageni able. available d enicity Bas tive toxic	ation Based on available data, the classification criteria are not met. e/irritation Based on available data, the classification criteria are not met. sensitisation Based on available data, the classification criteria are not met		

(Contd. on page 7)



Printing date 22.03.2025

Version number 37 (replaces version 36)

Revision: 22.03.2025

Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT

(Contd. of page 6)

SECTION 12: Ecological information

· 12.1 Toxicity

- Aquatic toxicity: No further relevant information available.
- 12.2 Persistence and degradability No further relevant information available.
- · 12.3 Bioaccumulative potential No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- · vPvB: Not applicable.
- · 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

- 12.7 Other adverse effects
- · Additional ecological information:
- · General notes:

Do not allow undiluted product or large quantities of it to reach ground water, water course or sewage system.

SECTION 13: Disposal considerations

13.1 Waste treatment methods

Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

Disposal must be made according to official regulations.

- · Uncleaned packaging:
- Recommendation:

Packagings that may not be cleansed are to be disposed of in the same manner as the product.

SECTION 14: Transport information		
· 14.1 UN number or ID number		
· ADR/ADN, IMDG, IATA	not regulated	
· ADN	- not regulated	
 14.2 UN proper shipping name ADR/ADN, ADN, IMDG, IATA 	not regulated	
· 14.3 Transport hazard class(es)		
· ADR/ADN, ADN, IMDG, IATA		
· Class	not regulated	
· 14.4 Packing group · ADR/ADN, IMDG, IATA	not regulated	
· 14.5 Environmental hazards:		
· Marine pollutant:	No	
		(Contd. on page



Printing date 22.03.2025

Version number 37 (replaces version 36)

Revision: 22.03.2025

Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT

	(Contd. of page 7)
 14.6 Special precautions for user 	Not applicable.
 14.7 Maritime transport in bulk according IMO instruments 	g to Not applicable.
· Transport/Additional information:	Not dangerous according to the above specifications.
· UN "Model Regulation":	not regulated

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment – Annex II
- None of the ingredients is listed.

· REGULATION (EU) 2019/1148

 Annex I - RESTRICTED EXPLOSIVES PRECURSORS (Upper limit value for the purpose of licensing under Article 5(3))

None of the ingredients is listed.

Annex II - REPORTABLE EXPLOSIVES PRECURSORS

None of the ingredients is listed.

· Regulation (EC) No 273/2004 on drug precursors

None of the ingredients is listed.

 Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors

None of the ingredients is listed.

• **15.2 Chemical safety assessment:** A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

Relevant phrases

- H301 Toxic if swallowed.
- H302 Harmful if swallowed.
- H310 Fatal in contact with skin.
- H314 Causes severe skin burns and eye damage.
- H315 Causes skin irritation.
- H317 May cause an allergic skin reaction.
- H318 Causes serious eye damage.
- H319 Causes serious eye irritation.
- H330 Fatal if inhaled.

(Contd. on page 9)



Printing date 22.03.2025

Version number 37 (replaces version 36)

Revision: 22.03.2025

Trade name: BTK WOOD CONSTRUCT EXPRESS BO 250G*12 IT

(Contd. of page 8) H400 Very toxic to aquatic life. H410 Very toxic to aquatic life with long lasting effects. EUH071 Corrosive to the respiratory tract. Department issuing SDS: PSRA · Contact: PSRA Date of previous version: 20.05.2021 · Version number of previous version: 36 Abbreviations and acronyms: ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society) VOC: Volatile Organic Compounds (USA, EU) DNEL: Derived No-Effect Level (REACH) PNEC: Predicted No-Effect Concentration (REACH) LC50: Lethal concentration, 50 percent LD50: Lethal dose, 50 percent PBT: Persistent, Bioaccumulative and Toxic vPvB: very Persistent and very Bioaccumulative Acute Tox. 3: Acute toxicity – Category 3 Acute Tox. 4: Acute toxicity – Category 4 Acute Tox. 2: Acute toxicity – Category 2 Skin Corr. 1C: Skin corrosion/irritation – Category 1C Skin Irrit. 2: Skin corrosion/irritation – Category 2 Eye Dam. 1: Serious eye damage/eye irritation - Category 1 Skin Sens. 1: Skin sensitisation - Category 1 Skin Sens. 1A: Skin sensitisation - Category 1A Aquatic Acute 1: Hazardous to the aquatic environment - acute aquatic hazard - Category 1 Aquatic Chronic 1: Hazardous to the aquatic environment - long-term aquatic hazard - Category 1