

Printing date 22.03.2025 Version number 109 (replaces version 108) Revision: 22.03.2025

SECTION 1: Identification of the substance/mixture and of the company/ undertaking

· 1.1 Product identifier

· Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

• **1.2 Relevant identified uses of the substance or mixture and uses advised against** No further relevant information available.

· Application of the substance / the mixture Adhesive

• 1.3 Details of the supplier of the safety data sheet • Manufacturer/Supplier:

Bison International Dr.A.F.Philipsstraat 9 NL-4462 EW Goes PO Box 160 NL-4460 AD Goes tel. +31 88 3235700 fax. +31 88 3235800 e mail: sds@boltonadhesives.com

· Further information obtainable from: PSRA

· 1.4 Emergency telephone number:

Bison and Griffon products: +31 88 3235700. Operating hours mo-fr 08:00h-17:00h (CET) UHU products: + 49 (0) 30/19240 (Notruf). Operating hours mo-fr 08:00h-17:00h (CET)

For detailed information contact the national Poison Centre @ https://poisoncentres.echa.europa.eu/appointed-bodies

SECTION 2: Hazards identification

· 2.1 Classification of the substance or mixture

Classification according to Regulation (EC) No 1272/2008

The product is not classified, according to the CLP regulation.

- · 2.2 Label elements
- · Labelling according to Regulation (EC) No 1272/2008 Void
- · Hazard pictograms Void
- · Signal word Void
- Hazard statements Void
- · Additional information:
- EUH208 Contains mixture of 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1), 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction.
- EUH210 Safety data sheet available on request.
- · 2.3 Other hazards
- · Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- **vPvB:** Not applicable.

SECTION 3: Composition/information on ingredients

- · 3.2 Mixtures
- · Description: Adhesive

(Contd. on page 2)

EU -



Printing date 22.03.2025

Version number 109 (replaces version 108)

Revision: 22.03.2025

Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

	(Contd. of page 1)		
Dangerous components:			
CAS: 2634-33-5 EINECS: 220-120-9 Index number: 613-088-00-6 Reg.nr.: 01-2120761540-60- XXXX	 1,2-benzisothiazol-3(2H)-one Eye Dam. 1, H318; Aquatic Acute 1, H400; Aquatic Chronic 1, H410; Acute Tox. 4, H302; Skin Irrit. 2, H315; Skin Sens. 1, H317 Specific concentration limit: Skin Sens. 1;H317; C ≥ 0.05 % 	<0.025%	
CAS: 55965-84-9 Index number: 613-167-00-5 Reg.nr.: 01-2120764691-48- XXXX	mixture of 5-chloro-2-methyl-2H-isothiazol- 3-one [EC no. 247-500-7] and 2-methyl-2H- isothiazol-3-one [EC no. 220-239-6] (3:1)	≥0.00025-<0.0015%	

SECTION 4: First aid measures

· 4.1 Description of first aid measures

- · General information: No special measures required.
- · After inhalation:
- Supply fresh air; consult doctor in case of complaints.
- No special measures required.
- After skin contact: Generally the product does not irritate the skin.
- After eye contact: Rinse opened eye for several minutes under running water.
- After swallowing: If symptoms persist consult doctor.
- 4.2 Most important symptoms and effects, both acute and delayed
- No further relevant information available.
- 4.3 Indication of any immediate medical attention and special treatment needed

No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.
- 5.2 Special hazards arising from the substance or mixture No further relevant information available.

(Contd. on page 3)

⁻ EU



Printing date 22.03.2025

Version number 109 (replaces version 108)

Revision: 22.03.2025

(Contd. of page 2)

Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

· 5.3 Advice for firefighters

 \cdot **Protective equipment:** No special measures required.

SECTION 6: Accidental release measures

- · 6.1 Personal precautions, protective equipment and emergency procedures Not required.
- 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up: Send for recovery or disposal in suitable receptacles.
- Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).

6.4 Reference to other sections

No dangerous substances are released.

See Section 7 for information on safe handling.

See Section 8 for information on personal protection equipment.

See Section 13 for disposal information.

SECTION 7: Handling and storage

• 7.1 Precautions for safe handling No special precautions are necessary if used correctly.

· Information about fire - and explosion protection: No special measures required.

 \cdot 7.2 Conditions for safe storage, including any incompatibilities

· Storage:

· Requirements to be met by storerooms and receptacles: No special requirements.

- Information about storage in one common storage facility: Not required.
- Further information about storage conditions: None.

• Storage class: 12

· 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· 8.1 Control parameters

· Ingredients with limit values that require monitoring at the workplace:

The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace.

Dermal	-	thiazol-3(2H)-one	0.966 mg/kg bw/day	
Demai	Worker, dermal, longterm exposition			
	Consumer, dermal, longterm exposition		0.345 mg/kg bw/day	
Inhalative	Worker, inhalative, longterm exposition		6.81 mg/m³	
	Consumer, inhalative, longterm exposition		1.2 mg/m ³	
PNECs				
2634-33-5	1,2-benzisot	thiazol-3(2H)-one		
Fresh wate	er	0.00403 mg/l		
Fresh water sediment 0.0499 mg/kg dry weight				
Marine wa	ter	0.000403 mg/l		
				(Contd. on page



Printing date 22.03.2025 Version number 109 (replaces version 108)

Revision: 22.03.2025

Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

Marine sediment 0.00499 mg/kg dry weight Soil 3 mg/kg Sewage treatment plant 1.03 mg/l 55965-84-9 mixture of 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) Fresh water 0.00339 mg/l Fresh water sediment 0.027 mg/kg dry weight Marine water 0.0039 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR			(Contd. of page 3
Sewage treatment plant 1.03 mg/l Sewage treatment plant 1.03 mg/l S5965-84-9 mixture of 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) Fresh water 0.00339 mg/l Fresh water sediment 0.027 mg/kg dry weight Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals ment	Marine sediment	0.00499 mg/kg dry we	ight
55965-84-9 mixture of 5-chloro-2-methyl-2H-isothiazol-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) Fresh water 0.00339 mg/l Marine water 0.00339 mg/l Marine water 0.00339 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be			
methyl-2H-isothiazol-3-one [ÉC no. 220-239-6] (3:1) Fresh water 0.00339 mg/l Fresh water sediment 0.027 mg/kg dry weight Marine water 0.0039 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of g	Sewage treatment plant 1.03 mg/l		
Fresh water sediment 0.027 mg/kg dry weight Marine water 0.00339 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection Not required. Hand protection Not required. Hand protection Not required. Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material Ponetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).			
Marine water 0.00339 mg/l Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Fresh water	0.00339 mg/l	
Marine sediment 0.027 mg/kg dry weight Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Fresh water sediment	0.027 mg/kg dry weigh	nt
Soil 0.01 mg/kg Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Marine water	0.00339 mg/l	
Sewage treatment plant 0.23 mg/l Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Marine sediment	0.027 mg/kg dry weigh	nt
Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).	Soil	0.01 mg/kg	
 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1). 	Sewage treatment plant	0.23 mg/l	
Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not required. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minutes (Permeation according to EN 374 Part 3: Level 1).			he making were used as basis.
	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go	s of the material: > 0,12 ove material nicals mentioned below o EN 374 Part 3: Level oggles recommended du	2 mm 7 the penetration time has to be at least 10 minutes 1). uring refilling
SECTION 9: Physical and chemical properties	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic	s of the material: > 0,12 we material hicals mentioned below o EN 374 Part 3: Level ggles recommended du cal and chemical p	2 mm 7 the penetration time has to be at least 10 minutes 1). uring refilling roperties
9.1 Information on basic physical and chemical properties	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on basi	s of the material: > 0,12 we material hicals mentioned below o EN 374 Part 3: Level ggles recommended du cal and chemical p	2 mm 7 the penetration time has to be at least 10 minutes 1). uring refilling roperties
9.1 Information on basic physical and chemical properties General Information	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on basis General Information	s of the material: > 0,12 we material hicals mentioned below o EN 374 Part 3: Level ggles recommended du cal and chemical p	2 mm 7 the penetration time has to be at least 10 minutes 1). uring refilling roperties ical properties
9.1 Information on basic physical and chemical properties General Information Physical state Fluid	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on basi General Information Physical state	s of the material: > 0,12 we material hicals mentioned below o EN 374 Part 3: Level ggles recommended du cal and chemical p	2 mm 7 the penetration time has to be at least 10 minutes 1). uring refilling roperties Fluid
9.1 Information on basic physical and chemical properties General Information Physical state Fluid Colour: According to product specification	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on basi General Information Physical state Colour:	s of the material: > 0,12 we material hicals mentioned below o EN 374 Part 3: Level ggles recommended du cal and chemical p	2 mm 2 mm 2 the penetration time has to be at least 10 minutes 1). uring refilling roperties Fluid According to product specification
9.1 Information on basic physical and chemical properties General Information Physical state Fluid Colour: According to product specification Odour: Characteristic	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on basi General Information Physical state Colour: Odour:	s of the material: > 0,12 we material hicals mentioned below o EN 374 Part 3: Level ggles recommended du cal and chemical p	2 mm 2 mm 2 the penetration time has to be at least 10 minutes 1). uring refilling roperties cal properties Fluid According to product specification Characteristic
9.1 Information on basic physical and chemical properties General Information Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined.	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on basi General Information Physical state Colour: Odour threshold: Melting point/freezing	s of the material: > 0,12 we material nicals mentioned below o EN 374 Part 3: Level oggles recommended du cal and chemical p ic physical and chemi	2 mm 2 mm 2 the penetration time has to be at least 10 minutes 1). uring refilling roperties for a properties Fluid According to product specification Characteristic Not determined.
9.1 Information on basic physical and chemical properties General Information Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and Fluid	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on basi General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing p	s of the material: > 0,12 we material nicals mentioned below o EN 374 Part 3: Level oggles recommended du cal and chemical p ic physical and chemi	2 mm 2 mm 7 the penetration time has to be at least 10 minutes 1). uring refilling roperties For a set of the se
9.1 Information on basic physical and chemical properties General Information Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and 100 °C	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physical SECTION 9: Physical General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing p Boiling point or initial b	s of the material: > 0,12 we material nicals mentioned below o EN 374 Part 3: Level oggles recommended du cal and chemical p ic physical and chemi	2 mm 2 mm 2 the penetration time has to be at least 10 minutes 1). uring refilling roperties roperties Fluid According to product specification Characteristic Not determined. Undetermined. 100 °C
9.1 Information on basic physical and chemical properties General Information Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and 100 °C Flammability Not applicable.	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physical SECTION 9: Physical General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing p Boiling point or initial b boiling range Flammability	s of the material: > 0,12 we material hicals mentioned below o EN 374 Part 3: Level ggles recommended du cal and chemical p ic physical and chemi point: boiling point and	2 mm 2 mm 2 the penetration time has to be at least 10 minutes 1). uring refilling roperties roperties Fluid According to product specification Characteristic Not determined. Undetermined. 100 °C
9.1 Information on basic physical and chemical properties General Information Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and 100 °C	degradation Material of gloves Recommended thicknes Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according to Eye/face protection Go SECTION 9: Physic 9.1 Information on basi General Information Physical state Colour: Odour threshold: Melting point/freezing p Boiling point or initial b boiling range Flammability Lower and upper explored	s of the material: > 0,12 we material hicals mentioned below o EN 374 Part 3: Level ggles recommended du cal and chemical p ic physical and chemi point: boiling point and	2 mm 2 mm 2 the penetration time has to be at least 10 minutes 1). uring refilling roperties For properties Fluid According to product specification Characteristic Not determined. Undetermined. 100 °C Not applicable.



Printing date 22.03.2025 Version number 109 (replaces version 108)

Revision: 22.03.2025

Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

Fiash point: Not applicable. Decomposition temperature: Not determined. PH at 20 °C 7 Viscosity: Not determined. Dynamic: Not determined. Solubility water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Vapour pressure at 20 °C: 23 hPa Density at 20 °C: 1.09 g/cm ³ Relative density Density at 20 °C: 1.09 g/cm ³ Relative density Not determined. Vapour density Not determined. Product is not selfigniting. Explosive properties: Product does not present an explosion hazard. Solvent content: Water: 49.0 % Solids content: 48.0 % Change in condition Explosives Explosives Void Change in condition Explosives Explosives Void Flammable gases Void Self-neating substances and mixtures Void Self-neating substances and mixtures Void Substances and mixtures Void Substances and mixtures Void Oxidising gaids Void Oxidising liquids Void Oxidising liquids Void		(Contd. of page
Decomposition temperature: Not determined. pH at 20 °C 7 Viscosity: Kinematic viscosity Not determined. Solubility water: Not determined. Solubility water: Not determined. Solubility water: Not determined. Yapour pressure at 20 °C: 23 hPa Density and/or relative density Density and/or relative density Relative density Not determined. Yapour density Not determined. Yapour density Not determined. Yapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are no measurable or not relevant for the characterization of the mixture. Appearance: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Product is not selfigniting. Explosive properties: Product does not present an explosion hazard. Solvent content: Water: 49.0 % Solids content: 48.0 % Change in condition Evaporation rate Not determined. Information with regard to physical hazard classes Explosives Void Flammable gases Void Aerosols Void Self-reactive substances and mixtures Void Flammable liquids Void Pyrophoric liquids Void Self-reactive substances and mixtures Void Self-reactive substances and mixtures Void Self-reactive substances and mixtures Void Self-reactive substances and mixtures Void Oxidising gases in contact with water Void Oxidising solids Void Oxidising solids Void Self-reactive substances and mixtures Void Self-reactive substances and mixtures Void Oxidising solids Void Oxidising contex Void Oxidising solids Void Oxidising contex Void Oxidising collas Void Oxidising c	Upper:	
pH at 20 °C 7 Viscosity: 7 Viscosity: Not determined. Dynamic: Not determined. Solubility water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. 23 hPa Density and/or relative density Density and/or relative density Density at 20 °C: 23 hPa Density and/or relative density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are no measurable or not relevant for the characterization of the mixture. Appearance: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Product is not selfigniting. Explosive properties: Product of so not present an explosion hazard. Solvent content: Water: 49.0 % Solids content: 48.0 % Change in condition Evaporation rate Not determined. Information with regard to physical hazard classes Explosives Void Flammable gases Void Aerosols Void Flammable gases Void Self-reactive substances and mixtures Void Substances and mixtures Void Self-reactive substances and mixtures Void Substances and mixtures Void Substances and mixtures Void Self-reactive substances and mixtures Void Substances and mixtures Void Substances and mixtures Void Substances and mixtures Void S		Not applicable.
pH at 20 °C 7 Viscosity: 7 Viscosity: Not determined. Dynamic: Not determined. Solubility water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. 23 hPa Density and/or relative density Density and/or relative density Density at 20 °C: 23 hPa Density and/or relative density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are nor me as urable or not relevant for the characterization of the mixture. Appearance: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Product is not selfigniting. Explosive properties: Product does not present an explosion hazard. Solvent content: Water: 49.0 % Change in condition Evaporation rate Not determined. Information with regard to physical hazard classes Explosives Void Aerosols Void Aerosols Void Flammable gases Void Self-reactive substances and mixtures Void Pyrophoric liquids Void Self-reactive substances and mixtures Void Self-reactive substances and mixtures Void Self-reactive substances and mixtures Void Self-reactive substances and mixtures Void Oxidising solids Void Self-reactive substances and mixtures Void Oxidising solids Void		Not determined.
Kinematic viscosity Not determined. Dynamic: Not determined. Solubility water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log Value) Not determined. Vapour pressure at 20 °C: 23 hPa Density and/or relative density Density and/or relative density Not determined. Vapour density Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Explosive properties: Product does not present an explosion hazard. Solvent content: Water: 49.0 % Vaids content: 48.0 % Change in condition Explosives Void Explosives Void Flammable gases Void Gases Void Flammable solids Void Solustance		7
Dynamic:Not determined.Solubilitywater:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Vapour pressure at 20 °C:23 hPaDensity at 20 °C:1.09 g/cm³Relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.S.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture.Appearance:FluidForm:FluidImportant information on protection of health and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Solids content:48.0 %Change in conditionVoidExplosivesVoidFlammable gasesVoidAgressesVoidFlammable gasesVoidFlammable solidsVoidPyrophoric liquidsVoidSelf-reactive substances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising solidsVoidOxidising solidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising s	Viscosity:	
Dynamic:Not determined.Solubilitywater:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Vapour pressure at 20 °C:23 hPaDensity at 20 °C:1.09 g/cm³Relative densityNot determined.Vapour densityNot determined.Vapour densityNot determined.S.2 Other informationAll relevant physical data were determined for th mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture.Appearance: Form: Important information on protection of health and environment, and on safety. Ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Solids content:48.0 %Charage in conditionVoidExplosivesVoidInformation with regard to physical hazardVoidClassesVoidExplosivesVoidFlammable gasesVoidFlammable solidsVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-reactive substances and mixturesVoidSubstances and mixturesVoidPyrophoric liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquids <td>Kinematic viscosity</td> <td>Not determined.</td>	Kinematic viscosity	Not determined.
water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Vapour pressure at 20 °C: 23 hPa Density at 20 °C: 1.09 g/cm³ Relative density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture. Appearance: Fluid Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Ignition temperature: Product is not selfigniting. Solvent content: #30.0 % Solvent content: 49.0 % Solids content: 49.0 % Change in condition Explosives Explosives Void Flammable gases Void Cases Void Flammable solids Void Self-reactive substances and mixtures Void Pyrophoric solids Void Solids colids Void Change in condition Explosives	Dynamic:	Not determined.
Partition coefficient n-octanol/water (log Not determined. Vapour pressure at 20 °C: 23 hPa Density and/or relative density Density at 20 °C: Density at 20 °C: 1.09 g/cm³ Relative density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined data are no me as urable or not relevant for the characterization of the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Ignition temperature: Product does not present an explosion hazard. Solvent content: 49.0 % Solids content: 49.0 % Solids content: 49.0 % Explosives Void Information with regard to physical hazard classes Void Explosives Void Gases under pressure Void Gases under pressure Void Flammable gases Void Solids co	Solubility	
value)Not determined.Vapour pressure at 20 °C:23 hPaDensity and/or relative density1.09 g/cm³Relative densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture.Appearance:FluidForm:FluidImportant information on protection of health and environment, and on safety.Ignition temperature:Product does not present an explosion hazard.Solvent content:49.0 %Water:49.0 %Solids content:48.0 %Change in conditionExplosive sExplosivesVoidAerosolsVoidOxidising gasesVoidAerosolsVoidFlammable solidsVoidProphoric solidsVoidProphoric solidsVoidProphoric solidsVoidProphoric solidsVoidProphoric solidsVoidSelf-reactive substances and mixturesVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising l	water:	Not miscible or difficult to mix.
value)Not determined.Vapour pressure at 20 °C:23 hPaDensity and/or relative density1.09 g/cm³Relative densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture.Appearance:FluidForm:FluidImportant information on protection of health and environment, and on safety.Ignition temperature:Product does not present an explosion hazard.Solvent content:49.0 %Water:49.0 %Solids content:48.0 %Change in conditionExplosive sExplosivesVoidAerosolsVoidOxidising gasesVoidAerosolsVoidFlammable solidsVoidProphoric solidsVoidProphoric solidsVoidProphoric solidsVoidProphoric solidsVoidProphoric solidsVoidSelf-reactive substances and mixturesVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising l	Partition coefficient n-octanol/water (log	
Vapour pressure at 20 °C:23 hPaDensity and/or relative density1.09 g/cm³Relative densityNot determined.Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are no measurable or not relevant for the characterization of the mixture.Appearance: Form:FluidForm:FluidImportant information on protection of health and environment, and on safety. Ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Solvent content:48.0 %Change in conditionKall of determined.Information with regard to physical hazard classesVoidExplosivesVoidFlammable gasesVoidAerosolsVoidSelf-reactive substances and mixturesVoidFlammable liquidsVoidFlammable solidsVoidProphoric solidsVoidProphoric solidsVoidPyrophoric solidsVoidPyrophoric solidsVoidSelf-reactive substances and mixturesVoidSubstances and mixturesVoidOxidising gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solids <t< td=""><td></td><td>Not determined.</td></t<>		Not determined.
Density and/or relative density Density at 20 °C: 1.09 g/cm³ Relative density Not determined. Vapour density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Product is not selfigniting. Product does not present an explosion hazard. Solvent content: 49.0 % Solids content: 49.0 % Solids content: 48.0 % Change in condition Evaporation rate Evaporation rate Not determined. Information with regard to physical hazard classes Void Explosives Void Flammable gases Void Gases under pressure Void Flammable solids Void Pyrophoric solids Void Pyrophoric solids Void Pyrophoric solids Void Self-heat		
Density at 20 °C: 1.09 g/cm³ Relative density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Ignition temperature: Product is not selfigniting. Explosive properties: Product does not present an explosion hazard. Solvent content: 48.0 % Change in condition Explosives Explosives Void Flammable gases Void Flammable gases Void Flammable liquids Void Flammable solids Void Flammable solids Void Pyrophoric solids Void Oxidising liquids Void		
Relative density Not determined. Vapour density Not determined. 9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are no me as urable or not relevant for the characterization of the mixture. Appearance: Form: Form: Fluid Important information on protection of health and environment, and on safety. Ignition temperature: Ignition temperature: Product is not selfigniting. Explosive properties: Product does not present an explosion hazard. Solvent content: 49.0 % Solids content: 48.0 % Change in condition Explosives Explosives Void Classes Void Flammable gases Void Aerosols Void Oxidising gases Void Self-reactive substances and mixtures Void Pyrophoric liquids Void Pyrophoric solids Void Substances and mixtures Void Oxidising liquids Void Oxidising solids Void Oxidising solids Void Oxidising solids Void		1 09 g/cm ³
Vapour densityNot determined.9.2 Other informationAll relevant physical data were determined for the mixture. All non-determined data are no measurable or not relevant for the characterization of the mixture.Appearance: Form: Important information on protection of health and environment, and on safety. Ignition temperature: Explosive properties: Product does not present an explosion hazard. Solvent content: Water: Value: Val		
9.2 Other information All relevant physical data were determined for the mixture. All non-determined data are no measurable or not relevant for the characterization of the mixture. Appearance: Fluid Form: Fluid Important information on protection of health and environment, and on safety. Product is not selfigniting. Ignition temperature: Product does not present an explosion hazard. Solvent content: 49.0 % Solids content: 48.0 % Change in condition Explosives Explosives Void Information with regard to physical hazard classes Explosives Void Aerosols Void Gases under pressure Void Flammable solids Void Flammable solids Void Pyrophoric liquids Void Pyrophoric solids Void Self-reactive substances and mixtures Void Pyrophoric liquids Void Oxidising substances and mixtures Void Oxidising substances and mixtures Void Oxidising solids Void Oxidising solids Void Oxidising solids		
mixture. All non-determined data are normeasurable or not relevant for the characterization of the mixture. Appearance: Form: Fluid Important information on protection of health and environment, and on safety. Fluid Ignition temperature: Product is not selfigniting. Explosive properties: Product does not present an explosion hazard. Solvent content: 49.0 % Solids content: 48.0 % Change in condition Explosives Explosives Void Flammable gases Void Flammable gases Void Flammable solids Void Flammable solids Void Pyrophoric solids Void Pyrophoric solids Void Pyrophoric solids Void Self-heating substances and mixtures Void Substances and mixtures Void Substances and mixtures Void Substances and mixtures Void Oxidising ignidis Void Oxidising solids Void Substances and mixtures Void Oxidising liquids Void Oxidising	• •	
Appearance: Form: Fuid Form: Fuid Important information on protection of healt. Fuid Ignition temperature: Product is not selfigniting. Explosive properties: Product does not present an explosion hazard. Solvent content: 49.0 % Water: 49.0 % Solids content: 48.0 % Change in condition Explosives Explosives Void Classes Void Flammable gases Void Aerosols Void Solids conter pressure Void Flammable liquids Void Flammable liquids Void Flammable gases and mixtures Void Flammable solids Void Self-reactive substances and mixtures Void Pyrophoric liquids Void Substances and mixtures, which emit Flammable gases in contact with water Oxidising liquids Void Substances and mixtures, which emit Flamabale gases in contact with water Oxidising solids Void <td>9.2 Other information</td> <td></td>	9.2 Other information	
Appearance:FluidForm:FluidImportant information on protection of healthand environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Solvent content:49.0 %Water:49.0 %Change in conditiontermined.Evaporation rateNot determined.Information with regard to physical hazardclassesExplosivesVoidFlammable gasesVoidAerosolsVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSubstances and mixtures, which emitVoidItamable gases in contact with waterVoidOxidising liquidsVoidSubstances and mixturesVoidSubstances a		measurable or not relevant for the
Form:FluidImportant information on protection of health and environment, and on safety.Product is not selfigniting.Ignition temperature:Product does not present an explosion hazard.Solvent content:Product does not present an explosion hazard.Water:49.0 %Solids content:49.0 %Evaporation rateNot determined.Information with regard to physical hazardclassesVoidExplosivesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidPyrophoric liquidsVoidSelf-reactive substances and mixturesVoidPyrophoric solidsVoidSubstances and mixtures, which emitVoidGuising gases in contact with waterVoidOxidising solidsVoidOxidising solidsVoidPyrophoric solidsVoidOxidising solidsVoidSubstances and mixturesVoidOxidising solidsVoidOxidising		characterization of the mixture.
Form:FluidImportant information on protection of health and environment, and on safety.Product is not selfigniting.Ignition temperature:Product does not present an explosion hazard.Solvent content:Product does not present an explosion hazard.Water:49.0 %Solids content:48.0 %Change in conditionEvaporation rateEvaporation rateNot determined.Information with regard to physical hazardSolidclassesVoidExplosivesVoidGases under pressureVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSubstances and mixtures, which emitVoidSubstances and mixtures, which emitVoidCoxidising solidsVoidOxidising solids <t< td=""><td>Appearance:</td><td></td></t<>	Appearance:	
and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Solvent content:49.0 %Water:49.0 %Solids content:48.0 %Change in conditionEvaporation rateEvaporation rateNot determined.Information with regard to physical hazardclassesExplosivesVoidFlammable gasesVoidOxidising gasesVoidGases under pressureVoidFlammable iquidsVoidFlammable solidsVoidSelf-neative substances and mixturesVoidPyrophoric liquidsVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising solidsVoidOxidising solids<	Form:	Fluid
and environment, and on safety.Ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Solvent content:49.0 %Water:49.0 %Solids content:48.0 %Change in conditionEvaporation rateEvaporation rateNot determined.Information with regard to physical hazardclassesExplosivesVoidFlammable gasesVoidOxidising gasesVoidGases under pressureVoidFlammable iquidsVoidFlammable solidsVoidSelf-neative substances and mixturesVoidPyrophoric liquidsVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising solidsVoidOxidising solids<	Important information on protection of healt	
Ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Solvent content:49.0 %Water:49.0 %Solids content:48.0 %Change in conditionEvaporation rateEvaporation rateNot determined.Information with regard to physical hazardclassesExplosivesVoidFlammable gasesVoidAerosolsVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSelf-heating substances and mixturesVoidSelf-heating substances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising liquidsVoidOxidising solidsVoidOxidising solidsVoidOxidi		
Explosive properties:Product does not present an explosion hazard.Solvent content:49.0 %Water:49.0 %Solids content:48.0 %Change in conditionExporation rateInformation with regard to physical hazardInformation with regard to physical hazardInformation with regard to physical hazardExplosivesExplosivesVoidFlammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable solidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitIfammable gases in contact with waterflammable gases in contact with waterVoidOxidising solidsVoidOxidising solidsVoid </td <td></td> <td>Product is not selfigniting.</td>		Product is not selfigniting.
Solvent content:49.0 %Water:49.0 %Solids content:48.0 %Change in conditionEvaporation rateEvaporation rateNot determined.Information with regard to physical hazard classesVoidFlammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidGases in contact with waterVoidOxidising solidsVoidOxidising solidsVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoid		
Water:49.0 %Solids content:48.0 %Change in conditionEvaporation rateEvaporation rateNot determined.Information with regard to physical hazard classesVoidExplosivesVoidFlammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSelf-heating substances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOrganic peroxidesVoid		
Solids content:48.0 %Change in conditionNot determined.Evaporation rateNot determined.Information with regard to physical hazard classesVoidExplosivesVoidFlammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising liquidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoid		49.0 %
Change in conditionEvaporation rateNot determined.Information with regard to physical hazard classesVoidExplosivesVoidFlammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSelf-heating substances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising liquidsVoidOxidising solidsVoidOxidising solidsVoidOxidising solidsVoidOrganic peroxidesVoid		
Evaporation rateNot determined.Information with regard to physical hazard classesVoidExplosivesVoidFlammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSelf-heating substances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising solidsVoidOxidising solidsVoid		40.0 //
Information with regard to physical hazard classes Explosives Void Flammable gases Void Aerosols Void Oxidising gases Void Gases under pressure Void Flammable liquids Void Flammable solids Void Self-reactive substances and mixtures Void Self-reactive substances and mixtures Void Pyrophoric liquids Void Self-heating substances and mixtures Void Self-heating substances and mixtures Void Substances and Mixtures Void Oxidising liquids Void Oxidising solids Void		Not determined
classesExplosivesVoidFlammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidSelf-heating substances and mixturesVoidSelf-heating substances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidOxidising liquidsVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid	•	
ExplosivesVoidFlammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid		1
Flammable gasesVoidAerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid		
AerosolsVoidOxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixturesVoidSubstances and mixturesVoidSubstances and mixtures, which emitFlammable gases in contact with waterflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidVoidVoid		
Oxidising gasesVoidGases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid	Flammable gases	
Gases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidVoidVoidOrganic peroxidesVoid	Aerosols	
Gases under pressureVoidFlammable liquidsVoidFlammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidVoidVoidOrganic peroxidesVoid	Oxidising gases	Void
Flammable solidsVoidSelf-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid	Gases under pressure	Void
Self-reactive substances and mixturesVoidPyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid	Flammable liquids	Void
Pyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid	Flammable solids	Void
Pyrophoric liquidsVoidPyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid	Self-reactive substances and mixtures	Void
Pyrophoric solidsVoidSelf-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid		Void
Self-heating substances and mixturesVoidSubstances and mixtures, which emitVoidflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid		
Substances and mixtures, which emitflammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid		
flammable gases in contact with waterVoidOxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid		
Oxidising liquidsVoidOxidising solidsVoidOrganic peroxidesVoid		Void
Oxidising solids Void Organic peroxides Void		
Organic peroxides Void		
(Contd. on page	Oxidising solids	



Printing date 22.03.2025

Version number 109 (replaces version 108)

Revision: 22.03.2025

(Contd. of page 5)

Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

Corrosive to metals
 Desensitised explosives

Void Void

SECTION 10: Stability and reactivity

- **10.1 Reactivity** No further relevant information available.
- · 10.2 Chemical stability
- · Thermal decomposition / conditions to be avoided:
- No decomposition if used according to specifications.
- · 10.3 Possibility of hazardous reactions No dangerous reactions known.
- **10.4 Conditions to avoid** No further relevant information available.
- 10.5 Incompatible materials: No further relevant information available.
- · 10.6 Hazardous decomposition products: No dangerous decomposition products known.

SECTION 11: Toxicological information

- 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008
- \cdot Acute toxicity Based on available data, the classification criteria are not met.

· LD/LC50 values relevant for classification:

2634-33-5 1,2-benzisothiazol-3(2H)-one

Oral	LD50	670 mg/kg (rat)
	LD50	>2000 mg/kg (rat)
Inhalative	LC50/4 h	0.4 mg/l (rat)

- Primary irritant effect:
- · Skin corrosion/irritation Based on available data, the classification criteria are not met.
- Serious eye damage/irritation Based on available data, the classification criteria are not met.
- · Respiratory or skin sensitisation Based on available data, the classification criteria are not met.
- Germ cell mutagenicity
- Not applicable.

Based on available data, the classification criteria are not met.

- Carcinogenicity Based on available data, the classification criteria are not met.
- \cdot Reproductive toxicity Based on available data, the classification criteria are not met.
- STOT-single exposure Based on available data, the classification criteria are not met.
- · STOT-repeated exposure Based on available data, the classification criteria are not met.
- \cdot Aspiration hazard Based on available data, the classification criteria are not met.
- Additional toxicological information:
- · Acute effects (acute toxicity, irritation and corrosivity) Not applicable.
- · Sensitisation Not applicable.
- Repeated dose toxicity Not applicable.
- 11.2 Information on other hazards

· Endocrine disrupting properties

None of the ingredients is listed.

(Contd. on page 7)

ΕL



Printing date 22.03.2025 Version number 109 (replaces version 108)

Revision: 22.03.2025

Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

(Contd. of page 6)

SECTION 12: Ecological information

· 12.1 Toxicity

- Aquatic toxicity: No further relevant information available.
- 12.2 Persistence and degradability No further relevant information available.
- · 12.3 Bioaccumulative potential No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- · vPvB: Not applicable.
- · 12.6 Endocrine disrupting properties
- The product does not contain substances with endocrine disrupting properties.
- 12.7 Other adverse effects
- · Additional ecological information:
- · General notes:

Do not allow undiluted product or large quantities of it to reach ground water, water course or sewage system.

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

Disposal must be made according to official regulations.

- · Uncleaned packaging:
- Recommendation:

Packagings that may not be cleansed are to be disposed of in the same manner as the product.

SECTION 14: Transport informa	SECTION 14: Transport information		
· 14.1 UN number or ID number			
· ADR/ADN, IMDG, IATA	not regulated		
· ADN	- not regulated		
 14.2 UN proper shipping name ADR/ADN, ADN, IMDG, IATA 	not regulated		
· 14.3 Transport hazard class(es)			
· ADR/ADN, ADN, IMDG, IATA			
· Class	not regulated		
· 14.4 Packing group · ADR/ADN, IMDG, IATA	not regulated		
 14.5 Environmental hazards: Marine pollutant: 	No		
		(Contd. on page	



Printing date 22.03.2025 Version number 109 (replaces version 108)

Revision: 22.03.2025

Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

	(Contd. of page 7
• 14.6 Special precautions for user	Not applicable.
 14.7 Maritime transport in bulk according IMO instruments 	ng to Not applicable.
· Transport/Additional information:	Not dangerous according to the above specifications.
· UN "Model Regulation":	not regulated

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment – Annex II
- None of the ingredients is listed.

· REGULATION (EU) 2019/1148

 Annex I - RESTRICTED EXPLOSIVES PRECURSORS (Upper limit value for the purpose of licensing under Article 5(3))

None of the ingredients is listed.

Annex II - REPORTABLE EXPLOSIVES PRECURSORS

None of the ingredients is listed.

· Regulation (EC) No 273/2004 on drug precursors

None of the ingredients is listed.

 Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors

None of the ingredients is listed.

• **15.2 Chemical safety assessment:** A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

Relevant phrases

- H301 Toxic if swallowed.
- H302 Harmful if swallowed.
- H310 Fatal in contact with skin.
- H314 Causes severe skin burns and eye damage.
- H315 Causes skin irritation.
- H317 May cause an allergic skin reaction.
- H318 Causes serious eye damage.
- H319 Causes serious eye irritation.
- H330 Fatal if inhaled.

(Contd. on page 9)



Printing date 22.03.2025 Vers

Version number 109 (replaces version 108)

Revision: 22.03.2025

Trade name: BTK WOOD GLUE EXPRESS BO 250G*12 IT

(Contd. of page 8) H400 Very toxic to aquatic life. Very toxic to aquatic life with long lasting effects. H410 EUH071 Corrosive to the respiratory tract. Department issuing SDS: PSRA · Contact: PSRA Date of previous version: 05.01.2022 Version number of previous version: 108 · Abbreviations and acronyms: ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society) DNEL: Derived No-Effect Level (REACH) PNEC: Predicted No-Effect Concentration (REACH) LC50: Lethal concentration, 50 percent LD50: Lethal dose, 50 percent PBT: Persistent, Bioaccumulative and Toxic vPvB: very Persistent and very Bioaccumulative Acute Tox. 3: Acute toxicity – Category 3 Acute Tox. 4: Acute toxicity – Category 4 Acute Tox. 2: Acute toxicity – Category 2 Skin Corr. 1C: Skin corrosion/irritation - Category 1C Skin Irrit. 2: Skin corrosion/irritation - Category 2 Eye Dam. 1: Serious eye damage/eye irritation - Category 1 Skin Sens. 1: Skin sensitisation – Category 1 Skin Sens. 1A: Skin sensitisation – Category 1A Aquatic Acute 1: Hazardous to the aquatic environment - acute aquatic hazard - Category 1 Aquatic Chronic 1: Hazardous to the aquatic environment - long-term aquatic hazard - Category 1 FU