

Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

SECTION 1: Identification of the substance/mixture and of the company/ undertaking

1.1 Product identifier

· Trade name: BTK MS PRO GR CRT 290ML*12 IT

- **1.2 Relevant identified uses of the substance or mixture and uses advised against** No further relevant information available.
- · Application of the substance / the mixture Sealant
- 1.3 Details of the supplier of the safety data sheet • Manufacturer/Supplier:

Bison International Dr.A.F.Philipsstraat 9 NL-4462 EW Goes PO Box 160 NL-4460 AD Goes tel. +31 88 3235700 fax. +31 88 3235800 e mail: sds@boltonadhesives.com

· Further information obtainable from: PSRA

· 1.4 Emergency telephone number:

Bison and Griffon products: +31 88 3235700. Operating hours mo-fr 08:00h-17:00h (CET) UHU products: + 49 (0) 30/19240 (Notruf). Operating hours mo-fr 08:00h-17:00h (CET)

For detailed information contact the national Poison Centre @ https://poisoncentres.echa.europa.eu/appointed-bodies

SECTION 2: Hazards identification

· 2.1 Classification of the substance or mixture

Classification according to Regulation (EC) No 1272/2008

The product is not classified, according to the CLP regulation.

- · 2.2 Label elements
- · Labelling according to Regulation (EC) No 1272/2008 Void
- Hazard pictograms Void
- · Signal word Void
- · Hazard statements Void
- · Additional information:
- EUH208 Contains trimethoxyvinylsilane. May produce an allergic reaction.

EUH211 Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

- · 2.3 Other hazards During curing methanol (CAS 67-56-1) is produced.
- · Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- · **vPvB:** Not applicable.

SECTION 3: Composition/information on ingredients

- · 3.2 Mixtures
- · Description: Sealant

(Contd. on page 2)



Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

Trade name: BTK MS PRO GR CRT 290ML*12 IT

(Contd. of page 1) · Dangerous components: CAS: 2768-02-7 trimethoxyvinylsilane 1-2.5% EINECS: 220-449-8 🚸 Flam. Liq. 3, H226; 伙 Acute Tox. 4, H332 Reg.nr.: 01-2119513215-52 CAS: 52829-07-9 bis(2,2,6,6-tetramethyl-4-piperidyl) sebacate ≥0.25-<1% EINECS: 258-207-9 Reg.nr.: 01-2119537297-32 CAS: 2768-02-7 trimethoxyvinylsilane ≥0.1-<1% EINECS: 220-449-8 🚸 Flam. Lig. 3, H226; 🗘 Acute Tox. 4, H332; Skin Index number: 014-049-00-0 Sens. 1B, H317 Reg.nr.: 01-2119513215-52 • Additional information: For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

· 4.1 Description of first aid measures

- · General information: No special measures required.
- After inhalation:

Supply fresh air; consult doctor in case of complaints. No special measures required.

- After skin contact: Generally the product does not irritate the skin.
- After eye contact: Rinse opened eye for several minutes under running water.
- · After swallowing: If symptoms persist consult doctor.
- **4.2 Most important symptoms and effects, both acute and delayed** No further relevant information available.
- **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.
- 5.2 Special hazards arising from the substance or mixture
- No further relevant information available.
- 5.3 Advice for firefighters
- · Protective equipment: No special measures required.

SECTION 6: Accidental release measures

• 6.1 Personal precautions, protective equipment and emergency procedures Not required.

- · 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up: Send for recovery or disposal in suitable receptacles.

Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).

• 6.4 Reference to other sections

No dangerous substances are released.

See Section 7 for information on safe handling.

(Contd. on page 3)

EU



Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

(Contd. of page 2)

Trade name: BTK MS PRO GR CRT 290ML*12 IT

See Section 8 for information on personal protection equipment. See Section 13 for disposal information.

SECTION 7: Handling and storage

• **7.1 Precautions for safe handling** No special precautions are necessary if used correctly. • **Information about fire - and explosion protection:** No special measures required.

· 7.2 Conditions for safe storage, including any incompatibilities

· Storage:

· Requirements to be met by storerooms and receptacles: No special requirements.

- · Information about storage in one common storage facility: Not required.
- · Further information about storage conditions: None.
- Storage class: 10
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· 8.1 Control parameters

Ingredients with limit values that require monitoring at the workplace:

The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace.

|--|

DITLEO				
2768-02-7	′ trimethoxyvi	inylsilane		
Oral	Consumer, oral, longterm exposition		0.3 mg/kg bw/day (rat)	
Dermal	Worker, derm	nal, longterm exposition	3.9 mg/kg bw/day (rat)	
	Consumer, de	ermal, longterm exposition	7.8 mg/kg bw/day (rat)	
Inhalative	Worker, inhal	lative, longterm exposition	27.6 mg/m³ (rat)	
	Consumer, in	halative, longterm exposition	6.7 mg/m³ (rat)	
			18.9 mg/m³ (rabbit)	
2768-02-7	trimethoxyvi	inylsilane		
Oral	Consumer, oral, longterm exposition		0.3 mg/kg bw/day (rat)	
Dermal Worker, derm		nal, longterm exposition	3.9 mg/kg bw/day (rat)	
	Consumer, de	ermal, longterm exposition	7.8 mg/kg bw/day (rat)	
Inhalative	Worker, inhal	lative, longterm exposition	27.6 mg/m³ (rat)	
	Consumer, in	halative, longterm exposition	6.7 mg/m³ (rat)	
			18.9 mg/m³ (rabbit)	
PNECs	•		•	
2768-02-7	[′] trimethoxyvi	inylsilane		
Fresh water		0.4 mg/l (rat)		
Fresh water sediment		1.5 mg/kg dry weight (rat)		
Marine water		0.04 mg/l (rat)		
Marine sediment 0.		0.15 mg/kg dry weight (rat)		
Soil		0.06 mg/kg (rat)		
		1		(Contd. on page



Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

Trade name: BTK MS PRO GR CRT 290ML*12 IT

Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) 2768-02-7 trimethoxyvinylsilane Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Sevage treatment plant 6.6 mg/l (rat) General protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are	Courses the stars and a loss t	(Contd. of pag
2768-02-7 trimethoxyvinylsilane Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ th preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material Pontertation time of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation accord	• ·	
Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ th preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).	•	
Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Additional protection measures, such as personal protective equipment General protection measures, such as personal protective equipment General protection: General protection: Not necessary if room is well-ventilated. Hand protection Not necessary if room is well-ventilated. Hand protection: Not necessary if room is well-ventilated. Hand protection: Not necessary if room is well-ventilated. Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).	-	
Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).		
Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The usual resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).	Fresh water sediment	
Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. Activitianal information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).	Marine water	0.04 mg/l (rat)
Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).	Marine sediment	0.15 mg/kg dry weight (rat)
Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).	Soil	0.06 mg/kg (rat)
Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1).	Sewage treatment plant	6.6 mg/l (rat)
 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ th preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1). 	Sporadic release	2.4 mg/l (rat)
 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ th preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minute (Permeation according to EN 374 Part 3: Level 1). 	Additional information	The lists valid during the making were used as basis.
• Eyertace protection Goggles recommended during refilling	Selection of the alove m	naterial on consideration of the penetration times rates of diffusion and
	degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according t • Eye/face protection Go SECTION 9: Physic	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minu to EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties
	degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according t • Eye/face protection Go SECTION 9: Physic • 9.1 Information on bas	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minu to EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties
General Information	degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according t • Eye/face protection Go SECTION 9: Physic • 9.1 Information on bas • General Information	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minu- to EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties sic physical and chemical properties
· General Information · Physical state Fluid	degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according t • Eye/face protection Go SECTION 9: Physic • 9.1 Information on bas • General Information • Physical state	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minu- to EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties sic physical and chemical properties Fluid
General Information Physical state Fluid Colour: According to product specification	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according t Eye/face protection Go SECTION 9: Physic 9.1 Information on bas General Information Physical state Colour:	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minu- to EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties sic physical and chemical properties Fluid According to product specification
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined.	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of cherr (Permeation according t Eye/face protection Go SECTION 9: Physica 9.1 Information on bas General Information Physical state Colour: Odour: Odour threshold:	as of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minuto to EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties sic physical and chemical properties Fluid According to product specification Characteristic Not determined.
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined.	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of cherr (Permeation according t Eye/face protection Go SECTION 9: Physical 9.1 Information on bas General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing	ss of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minuto to EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties sic physical and chemical properties Fluid According to product specification Characteristic Not determined. point: Undetermined.
Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and Vertice	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according t Eye/face protection Go SECTION 9: Physical SECTION 9: Physical General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing Boiling point or initial	ss of the material: > 0,12 mm ove material nicals mentioned below the penetration time has to be at least 10 minuto to EN 374 Part 3: Level 1). oggles recommended during refilling cal and chemical properties sic physical and chemical properties Fluid According to product specification Characteristic Not determined. point: boiling point and
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and boiling range Undetermined.	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according t Eye/face protection Go SECTION 9: Physical SECTION 9: Physical General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing Boiling point or initial boiling range	ss of the material: > 0,12 mm hicals mentioned below the penetration time has to be at least 10 minuto to EN 374 Part 3: Level 1). boggles recommended during refilling cal and chemical properties sic physical and chemical properties Fluid According to product specification Characteristic Not determined. point: boiling point and Undetermined.
General InformationPhysical stateFluidColour:According to product specificationOdour:CharacteristicOdour threshold:Not determined.Melting point/freezing point:Undetermined.Boiling point or initial boiling point andUndetermined.boiling rangeUndetermined.FlammabilityNot applicable.	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according t Eye/face protection Go SECTION 9: Physical SECTION 9: Physical General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing Boiling point or initial boiling range Flammability	as of the material: > 0,12 mm by ematerial nicals mentioned below the penetration time has to be at least 10 minu- to EN 374 Part 3: Level 1). boggles recommended during refilling cal and chemical properties sic physical and chemical properties Fluid According to product specification Characteristic Not determined. point: boiling point and Undetermined. Not applicable.
General Information Fluid Physical state Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and Undetermined.	degradation Material of gloves Recommended thickness Nitrile rubber, NBR Penetration time of glo For the mixture of chem (Permeation according t Eye/face protection Go SECTION 9: Physic 9.1 Information on bas General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing Boiling point or initial boiling range Flammability Lower and upper explored	as of the material: > 0,12 mm by ematerial nicals mentioned below the penetration time has to be at least 10 minu- to EN 374 Part 3: Level 1). boggles recommended during refilling cal and chemical properties sic physical and chemical properties Fluid According to product specification Characteristic Not determined. boiling point and Undetermined. Not applicable. osion limit

(Contd. on page 5)

ΕU



Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

Trade name: BTK MS PRO GR CRT 290ML*12 IT

	(Contd. of page
Flash point:	237 °C
Decomposition temperature:	Not determined.
pH	Not determined.
Viscosity:	
Kinematic viscosity	Not determined.
Dynamic:	Not determined.
Solubility	
water:	Not miscible or difficult to mix.
Partition coefficient n-octanol/water (log	
value)	Not determined.
Vapour pressure:	Not determined.
Density and/or relative density	
Density at 20 °C:	1.48 g/cm ³
Relative density	Not determined.
Vapour density	Not determined.
9.2 Other information	All relevant physical data were determined for th
	mixture. All non-determined data are no
	measurable or not relevant for th
	characterization of the mixture.
Appearance:	
Form:	Fluid
Important information on protection of hea	llth
and environment, and on safety.	
Ignition temperature:	Product is not selfigniting.
Explosive properties:	Product does not present an explosion hazard.
Solvent content:	
Solids content:	100.0 %
Change in condition	
Evaporation rate	Not determined.
Information with regard to physical haza	
	ard
classes	
classes Explosives	Void
classes Explosives Flammable gases	Void Void
classes Explosives Flammable gases Aerosols	Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases	Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure	Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids	Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids	Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures	Void Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids	Void Void Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids	Void Void Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures	Void Void Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit	Void Void Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water	Void Void Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water Oxidising liquids	Void Void Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water Oxidising liquids Oxidising solids	Void Void Void Void Void Void Void Void
classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water Oxidising liquids	Void Void Void Void Void Void Void Void



Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

(Contd. of page 5)

Trade name: BTK MS PRO GR CRT 290ML*12 IT

Desensitised explosives

Void

SECTION 10: Stability and reactivity

- · 10.1 Reactivity No further relevant information available.
- · 10.2 Chemical stability
- · Thermal decomposition / conditions to be avoided:
- No decomposition if used according to specifications.
- \cdot 10.3 Possibility of hazardous reactions No dangerous reactions known.
- 10.4 Conditions to avoid No further relevant information available.
- **10.5 Incompatible materials:** No further relevant information available.
- 10.6 Hazardous decomposition products: Possible in traces.
- Additional information: During curing methanol (CAS 67-56-1) is produced.

SECTION 11: Toxicological information

- 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008
- \cdot Acute toxicity <code>Based</code> on available data, the classification criteria are not met.

		evant for classific			
Oral	LD50	6899 mg/kg (rat)			
Dermal	LD50	3158 mg/kg (rat)			
Inhalative	LC50/4 h	16.8 mg/l (rat)			
2768-02-7	trimethox	yvinylsilane			
Oral	LD50	6899 mg/kg (rat)			
Dermal	LD50	3158 mg/kg (rat)			
Inhalative	LC50/4 h	16.8 mg/l (rat)			
· Skin corre	osion/irrita	ation			
Componer	nt	CAS No. I	Method	Species	Conclusion
Vinyltrimet	hoxysilane	e 2768-02-7 (OECD No. 429	mouse, dermal	no sensitisation
Serious e	ye damag	e/irritation Based	on available data,	the classification	criteria are not met.
· Respirato · Germ cell			sed on available d	ata, the classificat	ion criteria are not met

- Not applicable.
- Based on available data, the classification criteria are not met.
- Carcinogenicity Based on available data, the classification criteria are not met.
- · Reproductive toxicity Based on available data, the classification criteria are not met.
- STOT-single exposure Based on available data, the classification criteria are not met.
- **STOT-repeated exposure** Based on available data, the classification criteria are not met.
- Aspiration hazard Based on available data, the classification criteria are not met.
- Additional toxicological information:
- Acute effects (acute toxicity, irritation and corrosivity) Not applicable.
- · Sensitisation Not applicable.
- · Repeated dose toxicity Not applicable.

(Contd. on page 7)

EU



Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

(Contd. of page 6)

Trade name: BTK MS PRO GR CRT 290ML*12 IT

· 11.2 Information on other hazards

• Endocrine disrupting properties

None of the ingredients is listed.

SECTION 12: Ecological information

· 12.1 Toxicity

- · Aquatic toxicity: No further relevant information available.
- · 12.2 Persistence and degradability No further relevant information available.
- 12.3 Bioaccumulative potential No further relevant information available.
- **12.4 Mobility in soil** No further relevant information available.
- 12.5 Results of PBT and vPvB assessment
- · PBT: Not applicable.
- · **vPvB:** Not applicable.
- 12.6 Endocrine disrupting properties
- The product does not contain substances with endocrine disrupting properties.
- 12.7 Other adverse effects
- · Additional ecological information:
- · General notes:

Do not allow product to reach ground water, water course or sewage system.

Danger to drinking water if even small quantities leak into the ground.

SECTION 13: Disposal considerations

- · 13.1 Waste treatment methods
- · Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

Disposal must be made according to official regulations.

- · Uncleaned packaging:
- Recommendation:

Packagings that may not be cleansed are to be disposed of in the same manner as the product.

14.1 UN number or ID number		
ADR/ADN, IMDG, IATA	not regulated	
	-	
ADN	not regulated	
14.2 UN proper shipping name		
ADR/ADN, ADN, IMDG, IATA	not regulated	
14.3 Transport hazard class(es)		
ADR/ADN, ADN, IMDG, IATA		
Class	not regulated	



Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

Trade name: BTK MS PRO GR CRT 290ML*12 IT

	(Contd. of page 7
 14.4 Packing group ADR/ADN, IMDG, IATA 	not regulated
 14.5 Environmental hazards: Marine pollutant: 	No
· 14.6 Special precautions for user	Not applicable.
 14.7 Maritime transport in bulk accordi IMO instruments 	ng to Not applicable.
· Transport/Additional information:	Not dangerous according to the above specifications.
· UN "Model Regulation":	not regulated

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- Directive 2012/18/EU
- Named dangerous substances ANNEX I None of the ingredients is listed.
- DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment – Annex II
- None of the ingredients is listed.
- · REGULATION (EU) 2019/1148
- · Regulation (EC) No 273/2004 on drug precursors

None of the ingredients is listed.

- Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors
- None of the ingredients is listed.
- 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

· Relevant phrases

- H226 Flammable liquid and vapour.
- H317 May cause an allergic skin reaction.
- H318 Causes serious eye damage.
- H332 Harmful if inhaled.
- H361f Suspected of damaging fertility.
- H400 Very toxic to aquatic life.
- H411 Toxic to aquatic life with long lasting effects.
- · Department issuing SDS: PSRA

· Contact: PSRA

(Contd. on page 9)



Printing date 29.07.2024

Version number 6 (replaces version 5)

Revision: 29.07.2024

Trade name: BTK MS PRO GR CRT 290ML*12 IT

of previous version: 22.01.2022	
n number of previous version: 5	
viations and acronyms:	
coord relatif au transport international des marchandises dangereuses par route (Europe national Carriage of Dangerous Goods by Road) nternational Maritime Code for Dangerous Goods	an Agreement Concerni
ternational Air Transport Association	
lobally Harmonised System of Classification and Labelling of Chemicals	
European Inventory of Existing Commercial Chemical Substances	
: European List of Notified Chemical Substances	
nemical Abstracts Service (division of the American Chemical Society)	
Derived No-Effect Level (RÈACH)	
Predicted No-Effect Concentration (REACH)	
ethal concentration, 50 percent	
ethal dose, 50 percent	
ersistent, Bioaccumulative and Toxic	
ery Persistent and very Bioaccumulative	
q. 3: Flammable liquids – Category 3	
ox. 4: Acute toxicity – Category 4	
n. 1: Serious eye damage/eye irritation – Category 1	
ns. 1B: Skin sensitisation – Category 1B	
Reproductive toxicity – Category 2	
Acute 1: Hazardous to the aquatic environment - acute aquatic hazard – Category 1 Chronic 2: Hazardous to the aquatic environment - long-term aquatic hazard – Category 2	2