

Printing date 25.07.2024

Version number 4 (replaces version 3)

Revision: 25.07.2024

SECTION 1: Identification of the substance/mixture and of the company/ undertaking

1.1 Product identifier

• Trade name: GRF PM SEAL AN CQ 280ML*12 L001

• **1.2 Relevant identified uses of the substance or mixture and uses advised against** No further relevant information available.

· Application of the substance / the mixture Adhesive

\cdot 1.3 Details of the supplier of the safety data sheet

Manufacturer/Supplier: Bison International Dr.A.F.Philipsstraat 9 NL-4462 EW Goes PO Box 160 NL-4460 AD Goes tel. +31 88 3235700 fax. +31 88 3235800 e mail: sds@boltonadhesives.com

• Further information obtainable from: PSRA

· 1.4 Emergency telephone number:

National Poisons Information Centre: +353 (1) 809 2166 (8.00 a.m. to 10.00 p.m. 7 days a week) Healthcare Professionals: +353 (1) 809 2566 (24 hour service)

SECTION 2: Hazards identification

· 2.1 Classification of the substance or mixture

· Classification according to Regulation (EC) No 1272/2008

The product is not classified, according to the CLP regulation.

- · 2.2 Label elements
- · Labelling according to Regulation (EC) No 1272/2008 Void
- · Hazard pictograms Void
- · Signal word Void
- · Hazard statements Void
- Additional information:
- EUH208 Contains N,N'-ethane-1,2-diylbis(12-hydroxyoctadecan-1-amide), trimethoxyvinylsilane. May produce an allergic reaction.
- 2.3 Other hazards During curing methanol (CAS 67-56-1) is produced.
- · Results of PBT and vPvB assessment
- · PBT: Not applicable.
- · **vPvB:** Not applicable.

SECTION 3: Composition/information on ingredients

· 3.2 Mixtures

· Description: Adhesive

· Dangerous components:

CAS: 2768-02-7
EINECS: 220-449-8
Reg.nr.: 01-2119513215-52

trimethoxyvinylsilane Flam. Lig. 3, H226; (1) Acute Tox. 4, H332

1-2.5%

(Contd. on page 2)



Printing date 25.07.2024

Version number 4 (replaces version 3)

Revision: 25.07.2024

Trade name: GRF PM SEAL AN CQ 280ML*12 L001

		(0	Contd. of page 1)
Γ	CAS: 123-26-2	N,N'-ethane-1,2-diylbis(12-hydroxyoctadecan-1-amide)	≥0.1-<1%
	Reg.nr.: 01-2120783565-42	Skin Sens. 1B, H317; Aquatic Chronic 3, H412	
	CAS: 2768-02-7	trimethoxyvinylsilane	≥0.1-<1%
	EINECS: 220-449-8 Index number: 014-049-00-0 Reg.nr.: 01-2119513215-52	♦ Flam. Liq. 3, H226;	
	CAS: 52829-07-9	bis(2,2,6,6-tetramethyl-4-piperidyl) sebacate	≥0.25-<1%
	EINECS: 258-207-9 Reg.nr.: 01-2119537297-32	♦ Repr. 2, H361f; ♦ Eye Dam. 1, H318; ♦ Aquatic Acute 1, H400; Aquatic Chronic 2, H411	
	CAS: 13463-67-7	titanium dioxide	<1%
	EINECS: 236-675-5	& Carc. 2, H351, EUH212	
	Index number: 022-006-00-2	· · · · · · · ·	
	Reg.nr.: 01-2119489379-17		
_	· Additional information: For	the wording of the listed hazard phrases refer to section '	16

Additional information: For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

· 4.1 Description of first aid measures

· General information: No special measures required.

• After inhalation:

Supply fresh air; consult doctor in case of complaints.

No special measures required.

- After skin contact: Generally the product does not irritate the skin.
- · After eye contact: Rinse opened eye for several minutes under running water.
- · After swallowing: If symptoms persist consult doctor.
- **4.2 Most important symptoms and effects, both acute and delayed** No further relevant information available.
- **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.
- 5.2 Special hazards arising from the substance or mixture
- No further relevant information available.
- · 5.3 Advice for firefighters
- · Protective equipment: No special measures required.

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Not required.
- 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up: Send for recovery or disposal in suitable receptacles.

Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).

(Contd. on page 3)



Printing date 25.07.2024

Version number 4 (replaces version 3)

Revision: 25.07.2024

(Contd. of page 2)

Trade name: GRF PM SEAL AN CQ 280ML*12 L001

· 6.4 Reference to other sections

See Section 7 for information on safe handling.

See Section 8 for information on personal protection equipment.

See Section 13 for disposal information.

SECTION 7: Handling and storage

• **7.1 Precautions for safe handling** No special precautions are necessary if used correctly. • **Information about fire - and explosion protection:** No special measures required.

· 7.2 Conditions for safe storage, including any incompatibilities

· Storage:

• Requirements to be met by storerooms and receptacles: No special requirements.

- · Information about storage in one common storage facility: Not required.
- Further information about storage conditions: None.

· Storage class: 10

• 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· 8.1 Control parameters

Ingredients with limit values that require monitoring at the workplace:

The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace.

· DNELs

DINELS				
2768-02-7	trimethoxyvi	nylsilane		
Oral	Consumer, or	al, longterm exposition	0.3 mg/kg bw/day (rat)	
Dermal	Worker, derm	al, longterm exposition	3.9 mg/kg bw/day (rat)	
	Consumer, de	ermal, longterm exposition	7.8 mg/kg bw/day (rat)	
Inhalative	Worker, inhal	ative, longterm exposition	27.6 mg/m³ (rat)	
	Consumer, in	halative, longterm exposition	6.7 mg/m³ (rat)	
			18.9 mg/m³ (rabbit)	
2768-02-7	trimethoxyvi	nylsilane		
Oral	Consumer, or	al, longterm exposition	0.3 mg/kg bw/day (rat)	
Dermal	Worker, derm	al, longterm exposition	3.9 mg/kg bw/day (rat)	
	Consumer, de	ermal, longterm exposition	7.8 mg/kg bw/day (rat)	
Inhalative	Worker, inhal	ative, longterm exposition	27.6 mg/m³ (rat)	
	Consumer, in	halative, longterm exposition	6.7 mg/m³ (rat)	
			18.9 mg/m³ (rabbit)	
· PNECs				
2768-02-7	trimethoxyvi	nylsilane		
Fresh wate	er	0.4 mg/l (rat)		
Fresh wate	er sediment	1.5 mg/kg dry weight (rat)		
Marine wa	ter	0.04 mg/l (rat)		
				(Contd. on page 4)

www.griffon.eu

IF



Version number 4 (replaces version 3) Printing date 25.07.2024

Revision: 25.07.2024

Trade name: GRF PM SEAL AN CQ 280ML*12 L001

preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material	Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) 2768-02-7 trimethoxyvinylsilane Fresh water 0.4 mg/l (rat) Marine water 0.4 mg/l (rat) Marine sediment 1.5 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporatic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. * Agropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usuprecautionary measures are to be adhered t	Marina andiment	(Contd. of page 3
Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) 2768-02-7 trimethoxyvirylsilane Fresh water 0.4 mg/l (rat) Amore sediment 1.5 mg/kg dry weight (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) - Additional information: The lists valid during the making were used as basis. - Seporer controls - Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment - General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. - Respiratory protection: Not necessary if room is well-ventilated. - Hand protection The usual procautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. -	Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) 2768-02-7 trimethoxyvinyIsilane Fresh water Fresh water ediment 1.5 mg/kg dry weight (rat) Marine sediment 0.4 mg/l (rat) Marine sediment 0.5 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Additional information: The lists valid during the making were used as basis. * A2 Exposure controls -24 mg/l (rat) Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not ne	warme seument	0.15 mg/kg dry weight (rat)
Sporadic release 2.4 mg/l (rat) 2768-02-7 trimethoxyvinylsilane Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Swage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. * 8.2 Exposure controls Adpropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR SECTION 9: Physical and	Sporadic release 2.4 mg/l (rat) 2768-02-7 trimethoxyvinylsilane Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Soil crelease 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 3.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The usual of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyeface protection Goggles recommended during refill		
2768-02-7 trimethoxyvinylsilane Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.66 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentione	2768-02-7 trimethoxyvinylsilane Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. • Adjoint and protective and hygienic measures: The usual procecution and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ to preparation. Selection of the glove material: > 0,12 mm Nitrile ruber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Park grey <	Sewage treatment plant	6.6 mg/l (rat)
Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 4.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protection measures, such as personal protective equipment General protection Marine water is and at the end of work. Respiratory protection: Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material Por the mixture of chemicals mentioned below the penetration time has to be at least 10 mint (Permeation according to EN 374 Part 3: Level 1). <td>Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls - Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ tor proparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetra</td> <td></td> <td></td>	Fresh water 0.4 mg/l (rat) Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls - Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ tor proparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetra		
Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Adpropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1).	Fresh water sediment 1.5 mg/kg dry weight (rat) Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual protection: Not necessary if room is well-ventilated. Hand protection Yhe glove material has to be impermeable and resistant to the product/ the substance/ th preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Matrial of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material Portection Goggles recommended during refilling Section on basic physical and chemical properties General Information Bark grey 9.1 Information on basic physical and chemical properties General Information Characteristic Odour: Characteristic		
Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Adpropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 mint (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Goggles recommended during refilling SECTI	Marine water 0.04 mg/l (rat) Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ th gregaration. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyeface protection Goggles recommended during refilling Section 9: Physical and chemical properties General Information on basic physical and		
Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection Not necessary if room is well-ventilated. Hand protection Material of glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Physical state Fluid <td>Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual protection: Not necessary if room is well-ventilated. Hand protection Not necessary if room is well-ventilated. Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyeface protection Goggles recommended during refilling Setortion 9: P</td> <td></td> <td></td>	Marine sediment 0.15 mg/kg dry weight (rat) Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual protection: Not necessary if room is well-ventilated. Hand protection Not necessary if room is well-ventilated. Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyeface protection Goggles recommended during refilling Setortion 9: P		
Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Exerction Segles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Dark grey Odour threshold:	Soil 0.06 mg/kg (rat) Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ tipreparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Fluid	Marine water	0.04 mg/l (rat)
Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) • Additional information: The lists valid during the making were used as basis. • Appropriate engineering controls No further data; see section 7. • Individual protection measures, such as personal protective equipment • General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. • Respiratory protection: Not necessary if room is well-ventilated. • Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation • Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR • Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). • Eyelface protection Goggles recommended during refilling • SECTION 9: Physical and chemical properties • General Information • Physical state • Colour: • Odour: • Odour: • Odour threshold: • Melting point/freezing point: • Undetermined.	Sewage treatment plant 6.6 mg/l (rat) Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protective and hygienic measures: The usual procautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ ti preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Characteristic Odour: Characteristic	Marine sediment	0.15 mg/kg dry weight (rat)
Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protection measures, such as personal protective equipment General protection measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Goggles recommended during refilling	Sporadic release 2.4 mg/l (rat) Additional information: The lists valid during the making were used as basis. 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ to preparation. Selection of the gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined.	Soil	0.06 mg/kg (rat)
Additional information: The lists valid during the making were used as basis. Additional information: The lists valid during the making were used as basis. Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Goggles recommended during refilling Secondum	Additional information: The lists valid during the making were used as basis. Additional information: The lists valid during the making were used as basis. Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protection measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyelface protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Physical state Colour: Colour	Sewage treatment plant	6.6 mg/l (rat)
8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eye/face protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Dark grey Odour: Characteristic Odour: Characteristic Odour: Not determined. Matetermined. Not determined. <td>8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ ti preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyeface protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Colour: Colou</td> <td>Sporadic release</td> <td>2.4 mg/l (rat)</td>	8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ ti preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyeface protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Colour: Colou	Sporadic release	2.4 mg/l (rat)
8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minu (Permeation according to EN 374 Part 3: Level 1). Eyefface protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Dark grey Odour: Characteristic Odour threshold: Not determined.	8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: The usual precautionary measures are to be adhered to when handling chemicals. Wash hands before breaks and at the end of work. Respiratory protection: Not necessary if room is well-ventilated. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ ti preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves Recommended thickness of the material: > 0,12 mm Nitrile rubber, NBR Penetration time of glove material For the mixture of chemicals mentioned below the penetration time has to be at least 10 minut (Permeation according to EN 374 Part 3: Level 1). Eyefface protection Goggles recommended during refilling SECTION 9: Physical and chemical properties General Information Physical state Colour: Characteristic Odour threshold: Not determined. Hand priotection Colour: Col	Additional information:	The lists valid during the making were used as basis.
• 9.1 Information on basic physical and chemical properties • General Information • Physical state Fluid • Colour: Dark grey • Odour: Characteristic • Odour threshold: Not determined. • Melting point/freezing point: Undetermined.	• 9.1 Information on basic physical and chemical properties • General Information • Physical state Fluid • Colour: Dark grey • Odour: Characteristic • Odour threshold: Not determined. • Melting point/freezing point: Undetermined. • Boiling point or initial boiling point and boiling range Undetermined.	preparation.	
General Information Fluid Physical state Fluid Colour: Dark grey Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined.	General Information Fluid Physical state Fluid Colour: Dark grey Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and boiling range Undetermined.	preparation. Selection of the glove m degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according to	aterial on consideration of the penetration times, rates of diffusion and th s of the material: > 0,12 mm ve material licals mentioned below the penetration time has to be at least 10 minute o EN 374 Part 3: Level 1).
· Odour: Characteristic · Odour threshold: Not determined. · Melting point/freezing point: Undetermined.	· Odour: Characteristic · Odour threshold: Not determined. · Melting point/freezing point: Undetermined. · Boiling point or initial boiling point and boiling range Undetermined.	preparation. Selection of the glove m degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according to • Eye/face protection Go	aterial on consideration of the penetration times, rates of diffusion and th s of the material: > 0,12 mm ve material nicals mentioned below the penetration time has to be at least 10 minute o EN 374 Part 3: Level 1). ggles recommended during refilling
• Melting point/freezing point: Undetermined.	· Melting point/freezing point: Undetermined. · Boiling point or initial boiling point and Undetermined. boiling range Undetermined.	preparation. Selection of the glove m degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according to • Eye/face protection Go SECTION 9: Physic • 9.1 Information on basi • General Information • Physical state	aterial on consideration of the penetration times, rates of diffusion and th s of the material: > 0,12 mm ve material nicals mentioned below the penetration time has to be at least 10 minute o EN 374 Part 3: Level 1). ggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid
	Boiling point or initial boiling point and Undetermined.	preparation. Selection of the glove m degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according to • Eye/face protection Go SECTION 9: Physic • 9.1 Information on basi • General Information • Physical state • Colour:	aterial on consideration of the penetration times, rates of diffusion and th s of the material: > 0,12 mm ve material nicals mentioned below the penetration time has to be at least 10 minute o EN 374 Part 3: Level 1). ggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid Dark grey
· Boiling point or initial boiling point and	boiling range Undetermined.	preparation. Selection of the glove m degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according to • Eye/face protection Go SECTION 9: Physic • 9.1 Information on basi • General Information • Physical state • Colour: • Odour: • Odour threshold:	aterial on consideration of the penetration times, rates of diffusion and th s of the material: > 0,12 mm ve material nicals mentioned below the penetration time has to be at least 10 minute o EN 374 Part 3: Level 1). rggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid Dark grey Characteristic Not determined.
		preparation. Selection of the glove m degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according to • Eye/face protection Go SECTION 9: Physic • 9.1 Information on basi • General Information • Physical state • Colour: • Odour: • Odour threshold:	aterial on consideration of the penetration times, rates of diffusion and th s of the material: > 0,12 mm ve material incals mentioned below the penetration time has to be at least 10 minute o EN 374 Part 3: Level 1). iggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid Dark grey Characteristic Not determined. point: Undetermined.
		preparation. Selection of the glove m degradation • Material of gloves Recommended thickness Nitrile rubber, NBR • Penetration time of glo For the mixture of chem (Permeation according to • Eye/face protection Go SECTION 9: Physic • 9.1 Information on basi • General Information • Physical state • Colour: • Odour: • Odour threshold: • Melting point/freezing p	aterial on consideration of the penetration times, rates of diffusion and the s of the material: > 0,12 mm we material icals mentioned below the penetration time has to be at least 10 minute o EN 374 Part 3: Level 1). ggles recommended during refilling cal and chemical properties ic physical and chemical properties Fluid Dark grey Characteristic Not determined. point: ooiling point and



Printing date 25.07.2024

Version number 4 (replaces version 3)

Revision: 25.07.2024

Trade name: GRF PM SEAL AN CQ 280ML*12 L001

	(Contd. of page
Lower and upper explosion limit	
Lower:	Not determined.
Upper:	Not determined.
Flash point:	>202 °C
Decomposition temperature:	Not determined.
pH	Not determined.
Viscosity:	
Kinematic viscosity	Not determined.
Dynamic at 20 °C:	75000 mPas
Solubility	
water:	Not miscible or difficult to mix.
Partition coefficient n-octanol/water (log	
value)	Not determined.
Vapour pressure:	Not determined.
Density and/or relative density	
Density at 20 °C:	1.428 g/cm³
Relative density	Not determined.
Vapour density	Not determined.
9.2 Other information	All relevant physical data were determined for th
	mixture. All non-determined data are no
	measurable or not relevant for th
	characterization of the mixture.
Appearance:	
Form:	Pasty
Important information on protection of healt	h
and environment, and on safety.	
Ignition temperature:	Product is not selfigniting.
Explosive properties:	Product does not present an explosion hazard.
Solvent content:	
Organic solvents:	0.0 %
Solids content:	74.6 %
Change in condition	
Evaporation rate	Not determined.
Information with regard to physical hazar	
classes	u de la companya de l
Explosives	Void
Flammable gases	Void
Aerosols	Void
Oxidising gases	Void
Gases under pressure	Void
Flammable liquids	Void
	Void
Flammable solids	Void Void
Flammable solids Self-reactive substances and mixtures	Void
Flammable solids Self-reactive substances and mixtures Pyrophoric liquids	Void Void
Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids	Void Void Void
Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures	Void Void
Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit	Void Void Void
Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids	Void Void Void



Printing date 25.07.2024

Version number 4 (replaces version 3)

Revision: 25.07.2024

Trade name: GRF PM SEAL AN CQ 280ML*12 L001

	(Contd. of page 5)
Void	
Void	
Void	
Void	
	Void Void

SECTION 10: Stability and reactivity

• **10.1 Reactivity** No further relevant information available.

10.2 Chemical stability

Thermal decomposition / conditions to be avoided:

No decomposition if used according to specifications.

• 10.3 Possibility of hazardous reactions No dangerous reactions known.

• **10.4 Conditions to avoid** No further relevant information available.

• 10.5 Incompatible materials: No further relevant information available.

• 10.6 Hazardous decomposition products: Possible in traces.

• Additional information: During curing methanol (CAS 67-56-1) is produced.

SECTION 11: Toxicological information

• **11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008** • **Acute toxicity** Based on available data, the classification criteria are not met.

	-		,		
LD/LC50	values rel	evant for classif	ication:		
2768-02-7	7 trimetho	kyvinylsilane			
Oral	LD50	6899 mg/kg (rat)		
Dermal	LD50	3158 mg/kg (rat)		
Inhalative	LC50/4 h	16.8 mg/l (rat)			
2768-02-7	rimethox	kyvinylsilane			
Oral	LD50	6899 mg/kg (rat)		
Dermal	LD50	3158 mg/kg (rat)		
Inhalative	LC50/4 h	16.8 mg/l (rat)			
13463-67	-7 titanium	n dioxide			
Oral	LD50	>20000 mg/kg (rat)		
Dermal	LD50	>10000 mg/kg (rabbit)		
Inhalative	LC50/4 h	>6.82 mg/l (rat)			
Compone Vinyltrime Serious e Respirato Germ cel Not applic Based on Carcinog	thoxysilane ye damag ory or skin I mutagen cable. available c enicity Ba	CAS No. e 2768-02-7 e/irritation Base sensitisation Base icity data, the classification sed on available	d on available data ased on available d ation criteria are no data, the classificat	lata, the classificat t met.	criteria are not met. ion criteria are not met. met.

(Contd. on page 7)



Printing date 25.07.2024

Version number 4 (replaces version 3)

Revision: 25.07.2024

Trade name: GRF PM SEAL AN CQ 280ML*12 L001

(Contd. of page 6)

• STOT-repeated exposure Based on available data, the classification criteria are not met.

• Aspiration hazard Based on available data, the classification criteria are not met.

Additional toxicological information:

· Acute effects (acute toxicity, irritation and corrosivity) Not applicable.

• Sensitisation Not applicable.

· Repeated dose toxicity Not applicable.

· 11.2 Information on other hazards

· Endocrine disrupting properties

None of the ingredients is listed.

SECTION 12: Ecological information

· 12.1 Toxicity

- Aquatic toxicity: No further relevant information available.
- **12.2 Persistence and degradability** No further relevant information available.
- **12.3 Bioaccumulative potential** No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- 12.5 Results of PBT and vPvB assessment
- · **PBT:** Not applicable.
- **vPvB:** Not applicable.
- 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

- · 12.7 Other adverse effects
- · Additional ecological information:
- · General notes:

Do not allow product to reach ground water, water course or sewage system. Danger to drinking water if even small quantities leak into the ground.

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

· Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

Disposal must be made according to official regulations.

- · Uncleaned packaging:
- **Recommendation:** Disposal must be made according to official regulations.

SECTION 14: Transport information		
 14.1 UN number or ID number ADR/ADN, IMDG, IATA 	not regulated -	
 14.2 UN proper shipping name ADR/ADN, IMDG, IATA 	not regulated	
		(Contd. on page



Printing date 25.07.2024

Version number 4 (replaces version 3)

Revision: 25.07.2024

Trade name: GRF PM SEAL AN CQ 280ML*12 L001

	(Contd. of page
· 14.3 Transport hazard class(es)	
· ADR/ADN, ADN, IMDG, IATA · Class	not regulated
· 14.4 Packing group · ADR/ADN, IMDG, IATA	not regulated
14.5 Environmental hazards:	Not applicable.
[·] 14.6 Special precautions for user	Not applicable.
 14.7 Maritime transport in bulk accordi IMO instruments 	i ng to Not applicable.
· Transport/Additional information:	Not dangerous according to the above specifications.
· UN "Model Regulation":	not regulated

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment – Annex II
- None of the ingredients is listed.

· REGULATION (EU) 2019/1148

· Regulation (EC) No 273/2004 on drug precursors

None of the ingredients is listed.

Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors

None of the ingredients is listed.

· 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

· Relevant phrases

- H226 Flammable liquid and vapour.
- H317 May cause an allergic skin reaction.
- H318 Causes serious eye damage.
- H332 Harmful if inhaled.
- H351 Suspected of causing cancer.
- H361f Suspected of damaging fertility.
- H400 Very toxic to aquatic life.

(Contd. on page 9)



Printing date 25.07.2024

Version number 4 (replaces version 3)

Revision: 25.07.2024

Trade name: GRF PM SEAL AN CQ 280ML*12 L001

(Contd. of page 8) H411 Toxic to aquatic life with long lasting effects. H412 Harmful to aquatic life with long lasting effects. EUH212 Warning! Hazardous respirable dust may be formed when used. Do not breathe dust. Department issuing SDS: PSRA · Contact: PSRA Date of previous version: 26.01.2024 · Version number of previous version: 3 · Abbreviations and acronyms: ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society) DNEL: Derived No-Effect Level (REACH) PNEC: Predicted No-Effect Concentration (REACH) LC50: Lethal concentration, 50 percent LD50: Lethal dose, 50 percent PBT: Persistent, Bioaccumulative and Toxic vPvB: very Persistent and very Bioaccumulative Flam. Liq. 3: Flammable liquids - Category 3 Acute Tox. 4: Acute toxicity – Category 4 Eye Dam. 1: Serious eye damage/eye irritation – Category 1 Skin Sens. 1B: Skin sensitisation – Category 1B Carc. 2: Carcinogenicity – Category 2 Repr. 2: Reproductive toxicity – Category 2 Aquatic Acute 1: Hazardous to the aquatic environment - acute aquatic hazard - Category 1 Aquatic Chronic 2: Hazardous to the aquatic environment - long-term aquatic hazard - Category 2 Aquatic Chronic 3: Hazardous to the aquatic environment - long-term aquatic hazard - Category 3